

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Anadarko Prod Co.</u>		Lease <u>Dagger Draw</u> Osage <u>1 SWD</u>		Well # <u>1</u>	
Location of Well	Unit <u>1495N</u> <u>225W</u> <u>E</u>	Section <u>22</u>	Township <u>19</u>	Range <u>25</u>	County <u>Eddy</u>
Drilling Contractor	<u>W.E.K.</u>		Type of Equipment <u>ROTARY</u>		

* = CSG. TO WITNESS

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cemen
<u>17 1/2</u>	<u>13 3/8</u>	<u>48#</u>	<u>NEW</u>	<u>350'</u>	<u>CIRC</u>
* <u>12 1/4"</u>	<u>8 5/8"</u>	<u>24#</u>	<u>NEW</u>	<u>1300'</u>	<u>CIRC.</u>
<u>7 7/8"</u>	<u>5 1/2"</u>	<u>15.5#</u>	<u>"</u>	<u>8100'</u>	<u>CIRC</u>

Casing Data:

Surface _____ joints of _____ inch _____ # Grade _____
(Approved) (Rejected) _____

Inspected by _____ date _____

Cementing Program

Size of hole 12 1/4 Size of Casing 10 5/8 Sacks cement required 250

Type of Shoe used Tex-Pat Float collar used Insert Btm 3 jts welded Yes

TD of hole 1330 Set 1332 Feet of 8 5/8 Inch 24 # Grade K-55

New-used csg. @ 1332 with 250 sacks neat cement around shoe

+ 450 sax Pace Setter lite additives 3% CC

Plug down @ 3:00 (AM) (PM) Date 10-9-84

Cement circulated Yes No. of Sacks 250

Cemented by Western Witnessed by BW Weaver

Temp. Survey ran @ _____ (AM) (PM) Date _____ top cement @ _____

Casing test @ _____ (AM) (PM) Date _____

Method Used _____ Witnessed by _____

Checked for shut off @ _____ (AM) (PM) Date _____

Method used _____ Witnessed by _____

Remarks: Loss zone @ 527 ft