

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Yates Pet. Corp.</u>		Lease <u>Triangle Ranch AAB 51</u>		Well # <u>1</u>	
Location of Well	Unit <u>B</u>	Section <u>24</u>	Township <u>19</u>	Range <u>23</u>	County <u>EDDY</u>
Drilling Contractor	<u>UNDES</u>		Type of Equipment <u>ROTARY</u>		

* = CSG. TO WITNESS

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cemen
<u>17 1/2"</u>	<u>13 3/8"</u>	<u>48#</u>	<u>NEW</u>	<u>350</u>	<u>CIRC</u>
* <u>12 1/4"</u>	<u>8 5/8"</u>	<u>24#</u>	<u>"</u>	<u>1150</u>	<u>CIRC</u>
<u>7 7/8"</u>	<u>5 1/2 or 4 1/2</u>	<u>15.5 - 17</u> <u>10.5 - 11.6</u>	<u>"</u>	<u>TD</u>	<u>400 SX.</u>

Casing Data:

Surface _____ joints of _____ inch _____ # Grade _____
(Approved) (Rejected) _____

Inspected by _____ date _____

Cementing Program

Size of hole 12 1/4 Size of Casing 8 5/8 Sacks cement required 600

Type of Shoe used Guide Float collar used inst. Btm 3 jts welded yes

TD of hole 1145 Set 1148 Feet of 8 5/8 Inch 24 # Grade J-55

(New) used csg. @ 1145 with 250 sacks neat cement around shoe C.I.C w/2% CaCl₂
+ 350 sax Pacasetter Lite additives 10# Hiceal, 1/4# flocele + 3% CaCl₂

Plug down @ 4:15 (AM) (PM) Date 12-22-84

Cement circulated Yes No. of Sacks 25

Cemented by Western Witnessed by Larry Brooks

Temp. Survey ran @ _____ (AM) (PM) Date _____ top cement @ _____

Casing test @ _____ (AM) (PM) Date _____

Method Used _____ Witnessed by _____

Checked for shut off @ _____ (AM) (PM) Date _____

Method used _____ Witnessed by _____

Remarks: _____