

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Expires 9-5-85

Operator <u>EXXON</u>		Lease <u>N.MEX. EP ST COM</u>		Well # <u>1</u>	
Location of Well	Unit <u>K</u>	Section <u>19</u>	Township <u>19</u>	Range <u>24</u>	County <u>EDDY</u>
Drilling Contractor <u>UNKNOWN</u>			Type of Equipment <u>ROTARY</u>		

* = CSG. TO WITNESS

APPROVED CASING

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>17 1/2</u>	<u>13 3/8</u>	<u>54.5</u>	<u>NEW</u>	<u>300</u>	<u>CIRC</u>
* <u>12 1/4</u>	<u>8 5/8</u>	<u>24.0</u>	<u>"</u>	<u>1700</u>	<u>CIRC</u>
<u>7 7/8</u>	<u>5 1/2</u>	<u>14.15.5, 17</u>	<u>"</u>	<u>8800</u>	<u>620</u>

Casing Data:

2 joints of 12 1/4 inch # 24 Grade K-55
(Approved) (Rejected)

Inspected by _____ date _____

Cementing Program

Size of hole 12 1/4 Size of Casing 8 5/8 Sacks cement required TOT: 1000
TPCIRC: 506

Type of Shoe used GUIDE Float collar used INST. Btm 3 jts welded YES

ID of hole 1725 Set 1721 Feet of 8 5/8 inch 24 # Grade K-55 [STC]

New-used csg. @ 1721 with 250 sacks neat cement around shoe + 2% GEL

+ 750 sack HALLI. LITE additives + .5 lb/sk. flocc, 5 #/sk. gilsonite

Plug down @ 9:00 AM (PM) Date 2% CaCl₂ 6/30/85

Cement circulated YES No. of Sacks 497

Cemented by HALLIBURTON Witnessed by Danny Brooks

Temp. Survey ran @ _____ (AM) (PM) Date _____ top cement @ _____

Casing test @ _____ (AM) (PM) Date _____

Method Used _____ Witnessed by _____

Checked for shut off @ _____ (AM) (PM) Date _____

Method used _____ Witnessed by _____

Remarks: _____