

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Expires 10-17-85

Operator <u>Fi-Ro Corp</u>		Lease <u>FoFo</u>		Well # <u>5</u>	
Location of Well	Unit <u>E</u>	Section <u>32</u>	Township <u>19</u>	Range <u>27</u>	County <u>Eddy</u>
Drilling Contractor	<u>Clyde Tidwell</u>		Type of Equipment <u>Cable Tool</u>		
* Witness <u>APPROVED CASING PROGRAM</u>					
Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
* <u>10</u>	<u>7</u>	<u>23</u> <u>10-50</u> #		<u>277</u> <u>400</u>	<u>130</u> surf.
Casing Data:					
Surface _____ joints of _____ inch # Grade _____					
(Approved) (Rejected) _____					
Inspected by _____ date _____					
Cementing Program					
Size of hole <u>10</u> Size of Casing <u>7"</u> Sacks cement required <u>60</u>					
Type of Shoe used <u>Tex-Rt</u> Float collar used <u>No Float</u> Btm 3 jts welded <u>yes</u>					
TD of hole <u>281</u> Set <u>277</u> Feet of <u>7</u> Inch <u>23</u> # Grade <u>J-55</u>					
New used csg. @ <u>277</u> with <u>100</u> sacks neat cement around shoe					
+ _____ sax _____ additives <u>2% CaCl</u>					
Plug down @ <u>11:30</u> (AM) (PM) Date <u>5-3-85</u>					
Cement circulated <u>yes</u> No. of Sacks <u>5</u>					
Cemented by <u>Denton</u> Witnessed by <u>BW Weaver</u>					
Temp. Survey ran @ _____ (AM) (PM) Date _____ top cement @ _____					
Casing test @ _____ (AM) (PM) Date _____					
Method Used _____ Witnessed by _____					
Checked for shut off @ _____ (AM) (PM) Date _____					
Method used _____ Witnessed by _____					
Remarks: <u>Drilled With Cable Tool Small amount of water @ 100ft</u>					