

Operator <u>Neaburg Prod Co</u>		Lease <u>Morris 26 E</u>		Well # <u>1</u>	
Location of Well	Unit <u>E</u>	Section <u>26</u>	Township <u>19</u>	Range <u>25</u>	County <u>Eddy</u>
Drilling Contractor	<u>Peterson Drilling</u>		Type of Equipment <u>Rotary</u>		
<p>* Witness * See Attached Permit <u>APPROVED CASING PROGRAM</u></p>					
Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
* <u>17 1/2 * 12 1/4</u>	* <u>8 5/8</u>	<u>24 #</u>		<u>1350</u>	<u>1700 Circ</u>
<u>7 7/8</u>	<u>4 1/2</u>	<u>11.60 #</u>		<u>9850</u>	
Casing Data:					
Surface <u>8</u> joints of <u>13 3/8</u> inch <u>54.5</u> # Grade <u>J55</u>					
<u>Approved</u> (Approved) (Rejected)					
Inspected by <u>Johnny Rolinson</u> date <u>2-2-89</u>					
Cementing Program					
Size of hole <u>17 1/2</u> Size of Casing <u>13 3/8</u> Sacks cement required					
Type of Shoe used <u>guide</u> Float collar used <u>yes</u> Btm 3 jts welded <u>yes</u>					
TD of hole <u>355</u> Set <u>355</u> Feet of <u>13 3/8</u> inch <u>54.5</u> # Grade <u>J55</u>					
New-used csg. @ <u>355</u> with <u>450</u> ^{+270 c/c} Sacks neat cement around shoe					
+ <u>100</u> sax <u>class C</u> additives <u>10 gals. 1/4 Flocelec 170 cc/l</u>					
Plug down @ <u>10:15</u> (AM) (PM) <u>(PM)</u> Date <u>Feb. 3, 1989</u>					
Cement circulated <u>No</u> No. of Sacks					
Cemented by <u>Haliburton</u> Witnessed by <u>JR</u>					
Temp. Survey ran @ (AM) (PM) Date top cement @ <u>65 ft.</u>					
Casing test @ (AM) (PM) Date					
Method Used Witnessed by					
Checked for shut off @ (AM) (PM) Date					
Method used Witnessed by					
Remarks: <u>Ran 4 yds. of ready mix</u>					