

FIELD REPORT FOR CEMENTING OF WELLS

OIL CONSERVATION DIVISION

Operator <u>Santa Fe Energy Oper.</u>		Lease <u>Parkway 36 State</u>		Well # <u>6</u>	
Location of Well	Unit <u>E</u>	Section <u>36</u>	Township <u>19</u>	Range <u>29</u>	County <u>Eddy</u>
Drilling Contractor	<u>T.B.D.</u>		Type of Equipment <u>Rotary</u>		

*** Witness** APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>14 3/4</u>	<u>* 10 3/4</u>	<u>40.5</u>		<u>350</u>	<u>Surf.</u>
<u>9 1/2</u>	<u>* 7</u>	<u>20.0</u>		<u>3200</u>	<u>Surf.</u>
<u>7 7/8</u>	<u>5 1/2</u>	<u>15.5</u>		<u>5000</u>	

Casing Data:

Surface _____ joints of _____ inch _____ # Grade _____
 _____ (Approved) (Rejected) _____

Inspected by _____ date _____

Cementing Program

Size of hole 9 1/2" Size of Casing 7" Sacks cement required _____

Type of Shoe used guide Float collar used yes Btm 3 jts welded yes

TD of hole 3184' Set 3184' Feet of 2" Inch 33 # Grade K-55

New-used csg. @ 3184' with 540 27% sacks neat cement around shoe
 + _____ sax _____ additives _____

Plug down @ 3:30 (AM) (PM) PM Date 5-12-89

Cement circulated No No. of Sacks - 0 -

Cemented by Western Co. Witnessed by Mike Stubblefield

Temp. Survey ran @ No (AM) (PM) Date _____ top cement @ _____

Casing test @ _____ (AM) (PM) Date _____

Method Used _____ Witnessed by _____

Checked for shut off @ _____ (AM) (PM) Date _____

Method used _____ Witnessed by _____

Remarks: * Cement bridge off while pumping plug down left 83 BBLs cement inside csg.

1822'
Lost circ. 2 2024'

1. Tag $\oslash$ 2490' w/100 sx Cl. C. 470cc
2. Tag $\oslash$ 2420' w/100 sx Cl C 470cc
3. Tag $\oslash$ 2370' w/100 sx Cl. C 470cc
4. Tag $\oslash$ 2143' w/100 sx Cl. C 470cc
5. Tag $\oslash$ 2176' w/60 sx Cl. C 470cc
6. Tag $\oslash$ 2206' w/35 sx Cl. C. 670cc
7. Tag $\oslash$ 2098' w/35 sx Cl. C. 670cc
8. Tag $\oslash$ 2012' w/35 sx Cl. C 670cc
9. Tag $\oslash$ 2012' w/35 sx Cl. C. 670cc
10. Tag $\oslash$ 1877' w/35 sx Cl C 670cc
11. Tag $\oslash$ 1766' w/100 sx Cl C 670cc
12. Tag $\oslash$ 1679' w/125 sx Cl C 670cc
13. Tag $\oslash$ 1301' w/500 sx pacesetter lite 10# salt
14. Tag $\oslash$ 644' w/133 sx pacesetter lite 10# salt
cement circulated to surface.