

FIELD REPORT FOR CEMENTING OF WELLS

OIL CONSERVATION DIVISION

Operator <u>Gates Petr Corp</u>		Lease <u>Huisache "AHI" St Com</u>		Well # <u>1</u>	
Location of Well	Unit <u>H</u>	Section <u>2</u>	Township <u>20</u>	Range <u>24</u>	County <u>Eddy</u>
Drilling Contractor	<u>NA</u>		Type of Equipment <u>Rotary</u>		

* Witness

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>14 3/4</u>	* <u>9 5/8</u>	<u>36# J-55</u>		<u>1200</u>	<u>925 Circ</u>
<u>8 3/4</u>	<u>7</u>	<u>26# K-55 + N-80</u>		<u>TD</u>	<u>400</u>
		<u>23# K-55</u>			

Casing Data:

Surface _____ joints of 9 5/8" inch 36 # Grade J-55

(Approved) (Rejected)

Inspected by M.S. date 3-30-90

Cementing Program

Size of hole 14 3/4" Size of Casing 9 5/8" Sacks cement required _____Type of Shoe used guide Float collar used inset Btm 3 jts welded yesTD of hole 1205' Set 1205' Feet of 9 5/8" inch 36 # Grade J-55New-used csg. @ 1205' with 200 270cc sacks neat cement around shoe+ 900 sac pacesetter Lite additives 10# Hyseal, 1/2# Celloseal, 270ccPlug down @ 9:30 (AM) (PM) Date 4-5-90Cement circulated yes No. of Sacks 50Cemented by Western Company Witnessed by Mike Stobblefield

Temp. Survey ran @ _____ (AM) (PM) Date _____ top cement @ _____

Casing test @ _____ (AM) (PM) Date _____

Method Used _____ Witnessed by _____

Checked for shut off @ _____ (AM) (PM) Date _____

Method used _____ Witnessed by _____

Remarks: _____

Baskets 566-348'