

## FIELD REPORT FOR CEMENTING OF WELLS

OIL CONSERVATION DIVISION

Operator <u>Yates Petr. Corp</u>		Lease <u>Parish "IV" Com</u>		Well # <u>5</u>	
Location of Well	Unit <u>P</u>	Section <u>19</u>	Township <u>19</u>	Range <u>25</u>	County <u>Eddy</u>
Drilling Contractor	<u>NA</u>		Type of Equipment <u>Rotary</u>		

## APPROVED CASING PROGRAM

\* Witness

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>14 3/4</u>	* <u>9 5/8</u>	<u>36 # J-55</u>		<u>1100</u>	<u>1100</u>
<u>8 3/4</u>	<u>7</u>	<u>23-26 #</u>		<u>TD</u>	<u>As Warranted</u>
		<u>J-55 + N-80</u>			

## Casing Data:

Surface 25 joints of 9 5/8 inch 36 # Grade J-55

(Approved) (Rejected)

Inspected by Darrel Moore date 10/17/51

## Cementing Program

Size of hole 14 3/4 Size of Casing 9 5/8 Sacks cement required 900 sxsType of Shoe used guide Float collar used yes Btm 3 jts welded yesTD of hole 1090 Set 1097 Feet of 9 5/8 inch 36 # Grade J-55(New) used csg. @ 700 sxs PL with 200 sxs CH 2 1/2 sacks neat cement around shoe+ 370 sxs additives 10/10 #1 SK gilsonite + 1/2 # SK cell sealPlug down @ 10:45 (AM) (PM) Date 10/18/51Cement circulated yes No. of Sacks 150 sxs to pitCemented by Wooten Co Witnessed by Bo

Temp. Survey ran @ (AM) (PM) Date top cement @

Casing test @ (AM) (PM) Date

Method Used Witnessed by

Checked for shut off @ (AM) (PM) Date

Method used Witnessed by

Remarks: