

## FIELD REPORT FOR CEMENTING OF WELLS

OIL CONSERVATION DIVISION

Operator <u>Yates Petro Corp.</u>		Lease <u>Pincoshion</u>		Well # <u>3</u>	
Location of Well	Unit <u>N</u>	Section <u>30</u>	Township <u>19</u>	Range <u>25</u>	County <u>Eddy</u>
Drilling Contractor	<u>Ereder Dely Co rig # 24</u>		Type of Equipment <u>Rotary</u>		

## APPROVED CASING PROGRAM

\* Witness

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>14 3/4"</u>	<u>9 5/8"</u>	<u>36 # - J-55</u>		<u>1100'</u>	<u>1100 sx</u>
* <u>8 3/4"</u>	<u>7"</u>	<u>23-26 #</u>		<u>TD</u>	<u>As Wanted</u>

Casing Data:

Surface            joints of 9 5/8" inch 36 # Grade J-55

(Approved) (Rejected)

Inspected by n.s. date           

## Cementing Program

Size of hole 14 3/4" Size of Casing 9 5/8" Sacks cement required           Type of Shoe used guide Float collar used insert Btm 3 jts welded yesTD of hole 1129' Set 1129' Feet of 9 5/8" inch 36 # Grade J-55New/used csg. @ 1129' with 200 270cc sacks neat cement around shoe+ 700 sax pacesetter lite additives 10 # gilsonite, 1/4 # flo seal, 370ccPlug down @ 11:15 (AM) (PM) Date 10-27-91Cement circulated yes No. of Sacks 100 sxCemented by Western Company Witnessed by Mike StubblefieldTemp. Survey ran @            (AM) (PM) Date            top cement @           Casing test @            (AM) (PM) Date           Method Used            Witnessed by           Checked for shut off @            (AM) (PM) Date           Method used            Witnessed by           Remarks:           

Last dely break @ 1020'