

FIELD REPORT FOR CEMENTING OF WELLS

OIL CONSERVATION DIVISION

Operator <u>Yates Petr. Corp.</u>		Lease <u>John "AGU"</u>		Well # <u>5</u>	
Location of Well	Unit <u>F</u>	Section <u>14</u>	Township <u>20</u>	Range <u>24</u>	County <u>Eddy</u>
Drilling Contractor	<u>Undesignated</u>		Type of Equipment <u>Rotary</u>		

APPROVED CASING PROGRAM

X Witness

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>14 3/4</u>	<u>* 9 5/8</u>	<u>36# J-55</u>		<u>1100'</u>	<u>925 Circ</u>
<u>8 3/4</u>	<u>7</u>	<u>26# + 23# N-80</u>		<u>TD</u>	<u>400</u>

Casing Data:

Surface _____ joints of _____ inch _____ # Grade _____

(Approved) (Rejected)

Inspected by _____ date _____

Cementing Program

Size of hole 14 3/4" Size of Casing 9 5/8" Sacks cement required _____

Type of Shoe used guide Float collar used insert Btm 3 jts welded yes

TD of hole 1138' Set 1138' Feet of 9 5/8" inch 36 # Grade J-55

New-used csg. @ 1138' with 200 27 cc sacks neat cement around shoe

+ 800 sax Pacesetter Lite additives 10# gilsonite, 1/2# celoseal, 3% cc

Plug down @ 3:45 (AM) (PM) Date 12-12-91

Cement circulated yes No. of Sacks 100 cc

Cemented by Western Company Witnessed by Mike Stubblefield

Temp. Survey ran @ _____ (AM) (PM) Date _____ top cement @ _____

Casing test @ _____ (AM) (PM) Date _____

Method Used _____ Witnessed by _____

Checked for shut off @ _____ (AM) (PM) Date _____

Method used _____ Witnessed by _____

Remarks: _____