

FIELD REPORT FOR CEMENTING OF WELLS

OIL CONSERVATION DIVISION

Operator <u>Gates Petr. Corp.</u>		Lease <u>Binger "AKU"</u>		Well # <u>1</u>	
Location of Well	Unit <u>B</u>	Section <u>29</u>	Township <u>19</u>	Range <u>25</u>	County <u>Eddy</u>
Drilling Contractor	<u>NA</u>		Type of Equipment <u>Rotary</u>		

APPROVED CASING PROGRAM

Witness

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>14 3/4</u>	<u>* 9 5/8</u>	<u>36# J-55</u>		<u>1100</u>	<u>1100 Circ</u>
<u>8 3/4</u>	<u>7</u>	<u>23+26#</u>		<u>8300</u>	<u>As Warranted</u>
		<u>J-55, N-80</u>			

Casing Data:

Surface joints of 4 5/8" inch 36 # Grade J-55Approved (Rejected)Inspected by M.S. date July 2 - 1993

Cementing Program

Size of hole 14 3/4" Size of Casing 9 5/8" Sacks cement required Type of Shoe used guide Float collar used insert Btm 3 jts welded yesTD of hole 1163' Set 1163' Feet of 9 5/8" Inch 36 # Grade J-55New used csg. @ 1163' with 300 270 sacks neat cement around shoe+ 900 sax Pacesetter Lite C additives 10# gilsonite, 1/2# cellosol, 370ccPlug down @ 10:45 (AM) (PM) Date July 3 - 1993Cement circulated yes No. of Sacks 195Cemented by Western Company Witnessed by Mike StobblefieldTemp. Survey ran @ (AM) (PM) Date top cement @ Casing test @ (AM) (PM) Date Method Used Witnessed by Checked for shut off @ (AM) (PM) Date Method used Witnessed by Remarks: + 200 H 1270 Thixset (10# gilsonite, 1/2# cellosol, 270cc)

Last dily break 2 1072'