

Operator <u>Yates Petr.</u>		Lease <u>John AGU</u>		Well # <u>6</u>	
Location of Well	Unit <u>B</u>	Section <u>14</u>	Township <u>20</u>	Range <u>24</u>	County <u>Eddy</u>
Drilling Contractor	Type of Equipment				
<u>APPROVED CASING PROGRAM</u>					
Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
* <u>14 3/4</u>	<u>9 5/8</u>	<u>36#</u>	<u>New</u>	<u>7100'</u>	<u>1300</u>
<u>8 3/4</u>	<u>7</u>	<u>23+26#</u>			
Casing Data:					
Surface <u>24</u> joints of <u>9 5/8</u> inch <u>36</u> # Grade <u>J55</u>					
<u>yes</u> (Approved) (Rejected)					
Inspected by <u>J. Robinson</u> date <u>1-7-93</u>					
Cementing Program					
Size of hole <u>14 3/4</u> Size of Casing <u>9 5/8</u> Sacks cement required <u>1300</u>					
Type of Shoe used <u>Tex</u> Float collar used <u>yes</u> Btm 3 jts welded <u>yes</u>					
TD of hole <u>1075</u> Set <u>1085</u> Feet of <u>9 5/8</u> inch <u>36</u> # Grade <u>J55</u>					
New-used csg. @ _____ with <u>200</u> sacks neat cement around shoe <u>3% C.C.</u>					
+ <u>200</u> sack <u>ThiKset</u> additives <u>900srs lite 10# Gils. 1/2 celestic</u>					
Plug down @ _____ (AM) (PM) Date _____					
Cement circulated <u>NO</u> No. of Sacks _____					
Cemented by <u>Western Co.</u> Witnessed by <u>J. Robinson</u>					
Temp. Survey ran @ _____ (AM) (PM) Date <u>1-7-93</u> top cement @ <u>78 ft</u>					
Casing test @ _____ (AM) (PM) Date _____					
Method Used _____ Witnessed by _____					
Checked for shut off @ _____ (AM) (PM) Date _____					
Method used _____ Witnessed by _____					
Remarks: <u>Tagged top of cement @ 78'. Will ready mix.</u>					
<u>Last drlg break @ 933'</u>					