

10-22-93

FIELD REPORT FOR CEMENTING OF WELLS

OIL CONSERVATION DIVISION

30-015-27417

Operator <i>Conoco Inc.</i>		Lease <i>Barbara 17SW Com</i>		Well # <i>17</i>	
Location of Well	Unit <i>K</i>	Section <i>17</i>	Township <i>19</i>	Range <i>25</i>	County <i>Eddy</i>
Drilling Contractor <i>Exp. 3/17/94 - Under</i>	Type of Equipment <i>Rotary</i>				

APPROVED CASING PROGRAM

* *Witness*

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<i>13 1/2</i>	* <i>9 5/8</i>	<i>36#</i>		<i>1200'</i>	<i>1100 Sacks</i>
<i>8 3/4</i>	<i>7</i>	<i>26#</i>		<i>8100</i>	<i>1300</i>

Casing Data:

Surface _____ joints of *9 5/8"* inch *36* # Grade *K-55*

(Approved) (Rejected)

Inspected by *M.S.* date *Nov. 9-93*

Cementing Program

Size of hole *14 1/4"* Size of Casing *9 5/8"* Sacks cement required _____

Type of Shoe used *guide* Float collar used *insert* Btm 3 jts welded *yes*

TD of hole *1132'* Set *1132'* Feet of *9 5/8* Inch *36* # Grade *K-55*

~~New~~-used csg. @ *1132'* with *500 270cc* sacks neat cement around shoe

+ *900* sack *HAL. LTR* additives *1/2" floccul*, *370cc*

Plug down @ *9:30* (AM) (PM) Date *Nov. 9-93*

Cement circulated *No* No. of Sacks *-0-*

Cemented by *Halliburton* Witnessed by *milco Stubblefield*

Temp. Survey ran @ *1:30* (AM) (PM) Date *Nov. 9-93* top cement @ *300'*

Casing test @ _____ (AM) (PM) Date _____

Method Used _____ Witnessed by _____

Checked for shut off @ _____ (AM) (PM) Date _____

Method used _____ Witnessed by _____

Remarks: _____

Last dilg break @ 942'

1. Tag to c D 225' w/ 75 SX C 390 cc
2. Tag to c D 190' w/ 75 SX C 390 cc
3. Tag to c D 160' w/ 75 SX C 390 cc
4. Tag to c D 160' w/ 30 SX C 390 cc
5. Tag to c D 145' w/ 75 SX C 390 cc + 10 yards pea gravel
6. Tag to c D 145' w/ 50 SX C 390 cc + 10 yards pea gravel
7. Tag to c D 145' w/ 150 SX C 390 cc + 5 yards pea gravel