

FIELD REPORT FOR CEMENTING OF WELLS

OIL CONSERVATION DIVISION

30-015-27757

Operator <u>Gates Petr Corp</u>		Lease <u>Mobil "AOB"</u>		Well # <u>1</u>	
Location of Well	Unit <u>G</u>	Section <u>1</u>	Township <u>20</u>	Range <u>24</u>	County <u>Eddy</u>
Drilling Contractor	<u>NA</u>		Type of Equipment <u>Rotary</u>		

APPROVED CASING PROGRAM

* Witness

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
14 3/4	* 9 5/8	36# J-55		1100	1100 Circ
8 3/4	7	23 + 26 #		ID.	As Warranted
		J-55, N-80		8200	

Casing Data:

Surface _____ joints of 9 5/8" inch 36 # Grade J-55

(Approved) (Rejected)

Inspected by M.S. date Jan. 24-94

Cementing Program

Size of hole 14 3/4" Size of Casing 9 5/8" Sacks cement required _____Type of Shoe used guide Float collar used insert Btm 3 jts welded yesTD of hole 1095' Set 1095' Feet of 9 5/8" Inch 36 # Grade J-55(New) used csg. @ 1095' with 200 270 cc sacks neat cement around shoe+ 900 sax Pacesetter Lite C additives 10# gilsonite, 1/2# floeal, 370 ccPlug down @ 9:30 (AM) (PM) Date Jan. 25-94Cement circulated Yes No. of Sacks 140 sxCemented by Western Company Witnessed by Mike Stubblefield

Temp. Survey ran @ _____ (AM) (PM) Date _____ top cement @ _____

Casing test @ _____ (AM) (PM) Date _____

Method Used _____ Witnessed by _____

Checked for shut off @ _____ (AM) (PM) Date _____

Method used _____ Witnessed by _____

Remarks: + 200 sx 1270 Thixset - H 10# gilsonite, 1/2# floeal, 270 cc

L.C. - 247'

14 3/4" hole R.T. - 23 1/2 hrs

L.D.B. - 940'