

FIELD REPORT FOR CEMENTING OF WELLS

OIL CONSERVATION DIVISION

Operator <u>Jates Pet. Corp.</u>		Lease <u>Carl "TP" Com</u>		Well # <u>4</u>	
Location of Well	Unit <u>A</u>	Section <u>22</u>	Township <u>20</u>	Range <u>24</u>	County <u>Eddy</u>
Drilling Contractor	<u>NA</u>		Type of Equipment <u>Rotary</u>		

APPROVED CASING PROGRAM

Witness

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>14 3/4</u>	<u>* 9 5/8</u>	<u>36# J-55</u>		<u>1100'</u>	<u>1000 Circ</u>
<u>8 3/4</u>	<u>7</u>	<u>22-26 #</u>		<u>8250</u>	<u>As Warranted</u>
		<u>J-55 + N-80</u>		<u>TD</u>	

Casing Data:

Surface _____ joints of 9 5/8" inch 36 # Grade J-55

(Approved) (Rejected)

Inspected by M.S. date March 14-94

Cementing Program

Size of hole 14 3/4" Size of Casing 9 5/8" Sacks cement required _____

Type of Shoe used guide Float collar used insert Btm 3 jts welded yes

TD of hole 1025' Set 1025' Feet of 9 5/8" Inch 36 # Grade J-55

New used csg. @ 1025' with _____ sacks neat cement around shoe

+ 800 sax Pacemaker Lite - C additives 10# gilsonite, 5# celoseal, 3# ecc

Plug down @ 5:45 (AM) (PM) Date March 14-94

Cement circulated Yes No. of Sacks 198 sx

Cemented by Western Company Witnessed by Mike Stubblefield

Temp. Survey ran @ _____ (AM) (PM) Date _____ top cement @ _____

Casing test @ _____ (AM) (PM) Date _____

Method Used _____ Witnessed by _____

Checked for shut off @ _____ (AM) (PM) Date _____

Method used _____ Witnessed by _____

Remarks: +100sx CI H 1270 Thixset, 10# gilsonite, 1/2# celoseal.

L.D.B. - 935