

FIELD REPORT FOR CEMENTING OF WELLS

OIL CONSERVATION DIVISION

30-015-28033

Operator <u>Yates Petr. Corp</u>		Lease <u>Humble "ALD"</u>		Well # <u>1</u>	
Location of Well	Unit <u>G</u>	Section <u>28</u>	Township <u>19</u>	Range <u>25</u>	County <u>Eddy</u>
Drilling Contractor <u>NA</u>			Type of Equipment		

APPROVED CASING PROGRAM

* Witness

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>14 3/4</u>	* <u>9 5/8</u>	<u>36# J-55</u>		<u>1100'</u>	<u>1100 Circ</u>
<u>8 3/4</u>	<u>7</u>	<u>23# 26#</u>		<u>TD 8300</u>	<u>TD</u>
		<u>J-55, N-80</u>			

Casing Data:

Surface joints of 9 5/8" inch 36 # Grade J-55

(Approved) (Rejected)

Inspected by M.S. date

Cementing Program

Size of hole 14 3/4" Size of Casing 9 5/8" Sacks cement required Type of Shoe used guide Float coliar used insert Btm 3 jts welded yesTD of hole 1156' Set 1156' Feet of 9 5/8" Inch 36 # Grade J-55(New) used csg. @ 1156' with 200 27cc sacks neat cement around shoe+ 900 sax Western Lite additives 10# gilsonite, 1/4# floccal, 37ccPlug down @ 10:00 (AM) (PM) Date 10-20-94Cement circulated No No. of Sacks -0-Cemented by Western Company Witnessed by Mike StubblefieldTemp. Survey ran @ 3:00 (AM) (PM) Date 10/21/94 top cement @ 80' *Casing test @ (AM) (PM) Date Method Used Witnessed by Checked for shut off @ (AM) (PM) Date Method used Witnessed by Remarks:

L.C. - 63'

* Ready Mixed well to surface.

L.D.B. - 1060'