

WELL NAME: Serrano Federal #1

C E M E N T I N G P R O G R A M

SURFACE CASING STRING

LEAD	<u>900</u>	sxs	Class <u>C</u>	Mixed at <u>12.7</u> ppg
Additives	<u>3 % Gel + .5 pps Flocele + .5 pps Gibsonite</u>			
TAIL	<u>200</u>	sxs	Class <u>C</u>	Mixed at <u>14.8</u> ppg
Additives	<u>2 % CaCl</u>			

INTERMEDIATE CASING STRING

LEAD	_____	sxs	Class _____	Mixed at _____ ppg
Additives	_____			
TAIL	_____	sxs	Class _____	Mixed at _____ ppg
Additives	_____			

PRODUCTION CASING STRING

LEAD	<u>1200</u>	sxs	Class <u>C</u>	Mixed at <u>13.6</u> ppg
Additives	<u>5 pps Salt + .25 pps Flocele</u>			
TAIL	<u>100</u>	sxs	Class <u>C</u>	Mixed at <u>12.5</u> ppg
Additives	<u>2 % CaCl</u>			