

FIELD REPORT FOR CEMENTING OF WELLS

OIL CONSERVATION DIVISION

30-015-28424

Operator <u>Gates Petr. Corp</u>		Lease <u>Amole AMM St Com</u>		Well # <u>2</u>	
Location of Well	Unit <u>K</u>	Section <u>16</u>	Township <u>19</u>	Range <u>25</u>	County <u>Eddy</u>
Drilling Contractor	<u>N.A.</u>		Type of Equipment <u>Rotary</u>		

APPROVED CASING PROGRAM

* Witness

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>14 3/4</u>	* <u>9 5/8</u>	<u>36# J-55</u>		<u>1150</u>	<u>1100 Circ</u>
<u>8 3/4</u>	<u>7</u>	<u>23# 26#</u>		<u>TD</u>	<u>1350 Circ</u>
		<u>J-55, N-80</u>			

Casing Data:

Surface joints of 9 5/8 inch 36# = Grade J-55yes

(Approved) (Rejected)

Inspected by Ken Livingston date 5-17-95

Cementing Program

Size of hole 14 3/4 Size of Casing 9 5/8 Sacks cement required 1100 sxType of Shoe used Tex Float collar used insert Btm 3 jts welded yesTD of hole 1160' Set Feet of 9 5/8 inch 36# = Grade J-55New-used csg. @ with 200 27.00 sacks neat cement around shoe+ 900 sack P.L.C. additives gil. celo. 22.00Plug down @ 5:00 (AM) (PM) Date 5-17-95Cement circulated yes No. of Sacks 195 sxCemented by Western Witnessed by Ken Livingston

Temp. Survey ran @ (AM) (PM) Date top cement @

Casing test @ (AM) (PM) Date

Method Used Witnessed by

Checked for shut off @ (AM) (PM) Date

Method used Witnessed by

Remarks:

R.T. 25 1/2 hr, O.B. 969 + 1046, L.C. none