

## FIELD REPORT FOR CEMENTING OF WELLS

OIL CONSERVATION DIVISION

30-015-28747

|                                  |               |                          |                                 |                 |                    |
|----------------------------------|---------------|--------------------------|---------------------------------|-----------------|--------------------|
| Operator <u>Gates Petr. Corp</u> |               | Lease <u>Patrick API</u> |                                 | Well # <u>3</u> |                    |
| Location of Well                 | Unit <u>A</u> | Section <u>9</u>         | Township <u>19</u>              | Range <u>25</u> | County <u>Eddy</u> |
| Drilling Contractor              | <u>NA</u>     |                          | Type of Equipment <u>Rotary</u> |                 |                    |

## APPROVED CASING PROGRAM

\*Witness 9 5/8

| Size of Hole | Size of Casing | Weight Per Foot        | New or Used | Depth | Sacks Cement |
|--------------|----------------|------------------------|-------------|-------|--------------|
| 14 3/4       | * 9 5/8        | 36 # J-55              |             | 1150  | 1100 Circ    |
| 8 3/4        | 7              | 23 # + 26 # J-55, N-80 |             | TD    | 1350 Circ    |

## Casing Data:

Surface \_\_\_\_\_ joints of \_\_\_\_\_ inch \_\_\_\_\_ # Grade \_\_\_\_\_

(Approved) (Rejected) \_\_\_\_\_

Inspected by \_\_\_\_\_ date \_\_\_\_\_

## Cementing Program

Size of hole 14 3/4" Size of Casing 9 5/8" Sacks cement required \_\_\_\_\_Type of Shoe used guide Float collar used insert Btm 3 jts welded yesTD of hole 1160' Set 1160' Feet of 9 5/8" Inch 24 # Grade J-55(New) used csg. @ 1160' with 200 C-220 sacks neat cement around shoe  
+ 800 sax H/L-C additives 10 # gilsonite, 1/4 # floreal, 320 ccPlug down @ 6:45 (AM) (PM) (PM) Date 5-2-96Cement circulated yes No. of Sacks 205xCemented by B.J. Witnessed by Mike Stubblefield

Temp. Survey ran @ \_\_\_\_\_ (AM) (PM) Date \_\_\_\_\_ top cement @ \_\_\_\_\_

Casing test @ \_\_\_\_\_ (AM) (PM) Date \_\_\_\_\_

Method Used \_\_\_\_\_ Witnessed by \_\_\_\_\_

Checked for shut off @ \_\_\_\_\_ (AM) (PM) Date \_\_\_\_\_

Method used \_\_\_\_\_ Witnessed by \_\_\_\_\_

Remarks: +200 mixer - 5 # gilsonite, 1/2 # floreal, 220 cc

14 3/4" hole R.T. - 26 hrs.

L.D.B. - 1041