

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator Hanigan Petr. Corp.		Lease Catchlaw Draw Unit		Well # 7	
Location of Well	Unit 18505 16502	Section 14	Township 21	Range 25	County Eddy
Drilling Contractor Moran		Type of Equipment Rotary to start approx 10-1-72			
DV Test maybe used on 8 5/8"					
APPROVED CASING PROGRAM 10-2-72					
Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
17 1/2"	13 3/8"	54 + 61		300	Circ.
12 1/4" + 11"	8 5/8"	24		1900	Circ.
7 7/8"	5 1/2"	17			
Casing Data:					
Surface <u>48</u> joints of <u>8 5/8</u> inch <u>24</u> # Grade <u>J-55</u>					
(Approved) (Rejected)					
Inspected by <u>L. J. Gilman</u> date <u>10-11-72</u>					
Cementing Program					
Size of hole <u>12 1/4" to 7 1/8"</u> Size of Casing <u>8 5/8</u> Sacks cement required <u>800</u>					
Type of Shoe used <u>Guide Float collar</u> used <u>Insert</u> Btm 3 jts welded <u>welded</u>					
TD of hole <u>1855 KPS</u> Set <u>1844</u> Feet of <u>8 5/8</u> Inch <u>24</u> # Grade <u>J-55</u>					
New- used csg. @ <u>1544</u> with <u>150</u> sacks neat cement around shoe (Class C @ 2% CC @ Flowrec/ 2.7					
+ <u>650</u> sax <u>Halliburton</u> additives <u>5# Gilsenite</u> <u>1/4# Flowrec/</u> <u>2% CC</u> <u>14.8</u>					
Plug down @ <u>6:00</u> (AM) (PM) Date <u>10-12-72</u>					
Cement circulated <u>Yes</u> No. of Sacks <u>203 1/2</u>					
Cemented by <u>Halliburton</u> Witnessed by <u>L. J. Gilman</u>					
Temp. Survey ran @ (AM) (PM) Date top cement @					
Casing test @ (AM) (PM) Date					
Method Used Witnessed by					
Checked for shut off @ (AM) (PM) Date					
Method used Witnessed by					
Remarks: <u>Had to make trip at 1782. Lost circ. when started drlg.</u>					
<u>& TD. Spotted 200 bbls mad before running csg. and broke</u>					
<u>circ. will pump cement down.</u>					