

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER 10
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Pennycuik Co.</u>		Lease <u>meese com</u>		Well # <u>1</u>	
Location of Well	Unit <u>I</u> <u>23105</u> <u>6602</u>	Section <u>23</u>	Township <u>22</u>	Range <u>26</u>	County <u>Eddy</u>
Drilling Contractor			Type of Equipment <u>Rotary</u>		

APPROVED CASING PROGRAM 4-23-73

to start approx. 5-1-73

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>24"</u>	<u>20"</u>	<u>94#</u>		<u>375</u>	<u>400</u> <u>air.</u>
<u>17 1/2"</u>	<u>13 3/8"</u>	<u>48</u>		<u>2000</u>	<u>1800</u> <u>air.</u>
<u>12 1/4"</u>	<u>9 5/8"</u>	<u>36+40</u>		<u>5400</u>	<u>1800</u>
<u>8 1/2" - 7 7/8"</u>	<u>5 1/2"</u>	<u>17+20"</u>		<u>12500</u>	<u>1400</u>

Casing Data:

Surface 44 joints of 13 3/4 inch 48 # Grade API Ne
(Approved) (Rejected)

Inspected by L. A. Wimmer date

Cementing Program

Size of hole 17 1/2 Size of Casing 13 3/8 Sacks cement required 1800

Type of Shoe used Guide Float collar used Insert Btm 3 jts welded Threadlock

TD of hole 1924 ~~1910~~ feet of 13 3/8 inch 48 # Grade

New-used csg. @ 1910 with 200 sacks neat cement around shoe 1600 2% cc 4.8"
+ 1600 sack Lite additives 1/4" 10.5" 13.5"

Plug down @ 5:30 (AM) (PM) Date 7-3-73

Cement circulated NO No. of Sacks None

Cemented by B J Witnessed by L. A. Wimmer

Temp. Survey ran @ 2:00 (AM) (PM) Date 7-3-73 top cement @ 260'

Casing test @ (AM) (PM) Date

Method Used Witnessed by

Checked for shut off @ (AM) (PM) Date

Method used Witnessed by

Remarks: One inch 1st stage 100/sx Class C 2% cc 4.8", Second stage
Top 281' 150/sx Class C 2% cc 4.8", Third stage 20/sx same
in to surface.