

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <i>Logans Oil Corp.</i>		Lease <i>J M State</i>		Well # <i>1</i>	
Location of Well	Unit <i>1980s</i>	Section <i>11</i>	Township <i>21</i>	Range <i>27</i>	County <i>Eddy</i>
Drilling Contractor	<i>Cactus</i>		Type of Equipment <i>Rotary to start 9-1-73</i>		
APPROVED CASING PROGRAM					
Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<i>17 1/4</i>	<i>13 7/8</i>	<i>48</i>		<i>600</i>	<i>500 lbs.</i>
<i>12 1/4"</i>	<i>9 7/8"</i>	<i>36</i>		<i>3000</i>	<i>1200 Tons</i>
<i>8 3/4</i>	<i>7"</i>	<i>23-26-29</i>		<i>11700</i>	<i>500</i>
Casing Data:					
Surface <i>80</i> joints of <i>9 7/8</i> inch <i>36</i> # Grade <i>K-55 API New</i>					
(Approved) (Rejected)					
Inspected by <i>L. A. Mermis</i> date _____					
Cementing Program					
Size of hole <i>12 1/4 TD</i> Size of Casing <i>9 7/8</i> Sacks cement required <i>1300</i>					
Type of Shoe used <i>Guide</i> Float collar used <i>Insert</i> Btm <i>1</i> jts welded <i>2</i> threadlock					
TD of hole <i>3035</i> ft <i>3020</i> G Feet of <i>9 7/8</i> Inch <i>36</i> # Grade <i>K-55</i>					
New-used csg. @ <i>3020</i> G with <i>200</i> sacks neat cement around shoe <i>Class C 2% cc 14.8</i>					
+ <i>1100</i> sack <i>Class C</i> additives <i>50/50 Poz mix 5.5% salt 13.7</i>					
Plug down @ <i>11:10</i> (AM) (PM) Date <i>10-12-73</i>					
Cement circulated <i>80</i> Yes No. of Sacks <i>50/54</i>					
Cemented by <i>Halliburton</i> Witnessed by <i>L. A. Mermis</i>					
Temp. Survey ran @ _____ (AM) (PM) Date _____ top cement @ _____					
Casing test @ _____ (AM) (PM) Date _____					
Method Used _____ Witnessed by _____					
Checked for shut off @ _____ (AM) (PM) Date _____					
Method used _____ Witnessed by _____					
Remarks: _____					