

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>J. M. Huber Corp.</u>		Lease <u>Allied State Com.</u>		Well # <u>1</u>	
Location of Well	Unit <u>660N 1980W</u>	Section <u>14</u>	Township <u>21</u>	Range <u>27</u>	County <u>Eddy</u>
Drilling Contractor <u>Big West Drilling Co.</u>		Type of Equipment <u>Rotary to start 5-1-74</u>			
APPROVED CASING PROGRAM					
Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>17 1/2"</u>	<u>13 3/8"</u>	<u>48 + 61</u>		<u>600</u>	<u>750 Cmc</u>
<u>12 1/4"</u>	<u>9 5/8"</u>	<u>36</u>		<u>3000</u>	<u>1200 "</u>
<u>8 3/4"</u>	<u>4 1/2"</u>	<u>10.5 + 11.6</u>		<u>11800</u>	<u>750</u>
Casing Data:					
Surface <u> </u> joints of <u>9 5/8</u> inch <u>36</u> # Grade <u>New API K-55</u> <u>STC</u> (Approved) (Rejected)					
Inspected by <u> Not stamp</u> date <u> </u>					
Cementing Program					
Size of hole <u>12 1/2</u> Size of Casing <u>9 5/8</u> Sacks cement required <u>1200</u>					
Type of Shoe used <u>Guide</u> Float collar used <u>Insert</u> Btm <u>2</u> jts <u>welded</u>					
TD of hole <u>3000</u> Set <u>2982</u> Feet of <u>9 5/8</u> inch <u>36</u> # Grade <u>K-55</u>					
New-used csg. @ <u>2982</u> with <u>300</u> sacks neat cement around shoe <u>Class C</u> <u>Neat</u> <u>4.8</u>					
+ <u>900</u> sax <u>Slit Water</u> additives <u>73" salt</u> <u>1/2" Celloflake</u>					
Plug down @ <u>6:00</u> (AM) (PM) Date <u>5-16-74</u>					
Cement circulated <u>Yes</u> No. of Sacks <u>Over 100/51</u>					
Cemented by <u>Dowell</u> Witnessed by <u> </u>					
Temp. Survey ran @ <u> </u> (AM) (PM) Date <u> </u> top cement @ <u> </u>					
Casing test @ <u> </u> (AM) (PM) Date <u> </u>					
Method Used <u> </u> Witnessed by <u> </u>					
Checked for shut off @ <u> </u> (AM) (PM) Date <u> </u>					
Method used <u> </u> Witnessed by <u> </u>					
Remarks: <u>Surface 17 1/2" hole to 600' 13 3/8" 48# H-40 API New</u>					
<u>Insert 2 Cmc. 300/54 Class C 2% cc 1/2" Celloflake</u>					
<u>400/54 Class C 2% cc 1/4 Celloflake. Cmc.</u>					
<u>Baskets on 9 5/8" 1216', 864' Lost zone 850'-60'</u>					