

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

| | | | | | |
|---------------------------------|---------------------|----------------------------|--|-----------------|--------------------|
| Operator <u>Service Oil Co.</u> | | Lease <u>Tracy D. Com.</u> | | Well # <u>1</u> | |
| Location of Well | Unit <u>19805+W</u> | Section <u>33</u> | Township <u>21</u> | Range <u>27</u> | County <u>Eddy</u> |
| Drilling Contractor | | | Type of Equipment <u>Rotary to start approx. 11-1-75</u> | | |

* witness

APPROVED CASING PROGRAM

| Size of Hole | Size of Casing | Weight Per Foot | New or Used | Depth | Sacks Cement |
|------------------|----------------|-----------------|-------------|--------------|-----------------|
| <u>17 1/2"</u> | <u>13 7/8"</u> | <u>48</u> | | <u>400</u> | <u>500 ctn.</u> |
| * <u>12 1/4"</u> | <u>9 5/8"</u> | <u>36</u> | | <u>3000</u> | <u>1000 "</u> |
| <u>8 3/4"</u> | <u>5 1/2"</u> | <u>17+20</u> | | <u>11600</u> | <u>600</u> |

Casing Data:

Surface _____ joints of _____ inch _____ # Grade _____
(Approved) (Rejected) _____

Inspected by _____ date _____

Cementing Program

Size of hole 12 1/4 Size of Casing 9 5/8 Sacks cement required _____

Type of Shoe used Guide Float collar used YES Btm 3 jts welded LOK

TD of hole 3000 Set _____ Feet of 9 5/8 Inch 36 # Grade 4-55

New-~~used~~ csg. @ 3000 LB with 200 sacks neat cement around shoe 2% PAC 12
+ 875 sax Howell LITE additives 5# GILS. 1/4" FLO CELL

Plug down @ 1140 (AM) (PM) Date 10-13-75

Cement circulated YES No. of Sacks 75

Cemented by HALLIBURTON ~~CHECKED~~ by John R. Broughton

Temp. Survey ran @ _____ (AM) (PM) Date _____ top cement @ _____

Casing test @ _____ (AM) (PM) Date _____

Method Used _____ Witnessed by _____

Checked for shut off @ _____ (AM) (PM) Date _____

Method used _____ Witnessed by _____

Remarks: _____