

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <i>Truckee Water Co. Inc.</i>		Lease <i>City of Carlsbad Supply</i>		Well # <i>1</i>	
Location of Well	Unit <i>H</i> <i>2242N</i> <i>330E</i>	Section <i>36</i>	Township <i>22</i>	Range <i>26</i>	County <i>Eddy</i>
Drilling Contractor			Type of Equipment <i>Cable tools</i>		

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<i>12 1/4"</i>	<i>8 5/8"</i>	<i>24</i>		<i>350</i>	<i>150 cins.</i>
<i>7 7/8"</i>	<i>5 1/2"</i>	<i>15.5</i>		<i>650</i>	<i>200 cins.</i>

Casing Data:

Surface *13* joints of *8 5/8* inch *32* # Grade *J-55*

(Approved) (~~Rejected~~)

Inspected by *Nick Tinker* date _____

Cementing Program

Size of hole *10"* Size of Casing *8 5/8* Sacks cement required *225*

Type of Shoe used _____ Float collar used _____ Btm 3 jts welded _____

TD of hole *350'* Set *350'* Feet of *8 5/8* Inch *32* # Grade *J-55*

New-~~sg.~~ csg. @ *350'* with *225* sacks neat cement around shoe

+ _____ sax _____ additives *2% gel*

Plug down @ *1:30* (~~PM~~) Date *7-17-96*

Cement circulated *Yes* No. of Sacks *0*

Cemented by *Dowell* Witnessed by *Nick Tinker*

Temp. Survey ran @ _____ (AM) (PM) Date _____ top cement @ _____

Casing test @ _____ (AM) (PM) Date _____

Method Used _____ Witnessed by _____

Checked for shut off @ _____ (AM) (PM) Date _____

Method used _____ Witnessed by _____

Remarks: *Cement circulated but settled back about 12' so used ready-mix to surface.*