

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Norris R. Antweil</u>		Lease <u>Mesa Macho</u>		Well # <u>1</u>	
Location of Well	Unit <u>0</u> <u>6605</u> <u>1980e</u>	Section <u>24</u>	Township <u>20</u>	Range <u>27</u>	County <u>Eddy</u>
Drilling Contractor	<u>Motanco</u>		Type of Equipment <u>Rotary</u>		

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>17 1/2"</u>	<u>13 3/8"</u>	<u>48</u>		<u>650</u>	<u>600 circ</u>
<u>12 1/4"</u>	<u>9 5/8"</u>	<u>36</u>		<u>2600</u>	<u>1250 circ</u>
<u>8 3/4"</u>	<u>5 1/2"</u>	<u>17 & 20</u>		<u>11,400</u>	<u>550</u>

Casing Data:

Surface _____ joints of _____ inch _____ # Grade _____
(Approved) (Rejected) _____

Inspected by _____ date _____

Cementing Program

Size of hole 12 1/4" Size of Casing 9 5/8" Sacks cement required 1250

Type of Shoe used Halliburton Float collar used Halliburton Btm 3 jts welded Yes

TD of hole 2607 KB Set 2593 Feet of 9 5/8" Inch 36 # Grade N-80

New-used csg. @ 2593 GL with 300 sacks neat cement around shoe
+ 950 sax 150 5x Thix-sat additives Flexseal, Silomite & C-1

Plug down @ 5:00 (AM) (PM) Date 6-30-76

Cement circulated Yes No. of Sacks 1250

Cemented by Halliburton Witnessed by Dewey Green & Rick Tinker

Temp. Survey ran @ No (AM) (PM) Date 6-30-76 top cement @ circ.

Casing test @ _____ (AM) (PM) Date _____

Method Used _____ Witnessed by _____

Checked for shut off @ _____ (AM) (PM) Date _____

Method used _____ Witnessed by _____

Remarks: _____