

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Sulco Petroleum Corp.</u>		Lease <u>Pennycail State</u>		Well # <u>1</u>	
Location of Well	Unit <u>B</u> <u>913 N</u> <u>2193 E</u>	Section <u>16</u>	Township <u>22</u>	Range <u>25</u>	County <u>Eddy</u>
Drilling Contractor	<u>McVay</u>		Type of Equipment <u>factory to start 1-7-77</u>		

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>17 1/2"</u>	<u>13 3/8"</u>	<u>48</u>		<u>300</u>	<u>315 circ.</u>
<u>12 1/4"</u>	<u>9 5/8"</u>	<u>36</u>		<u>2300</u>	<u>750 circ.</u>
<u>8 1/2"</u>	<u>5 1/2"</u>	<u>17 + 20</u>		<u>16950</u>	<u>720</u>

Casing Data:

Surface 61 joints of 9 5/8 inch 36 # Grade API New J&K-55 STC Co Ltd
(Approved) (Rejected)

Inspected by Lelan Mermis date 1-28-77

Cementing Program

Size of hole 12 1/4" Size of Casing 9 5/8" Sacks cement required 1200/50

Type of Shoe used Slide Float collar used Yes Btm 2 jts welded Thread-Lock

TD of hole 2395 1/8 Set 2381 1/8 Feet of 9 5/8 Inch 36 # Grade J&K-55

New-used csg. @ 2381 1/8 with 200 sacks neat cement around shoe Class C 2%cc
+ 1000 / sax Class C 2% Indence additives 1/4" cello Flake

Plug down @ 9:30 (AM) (PM) Date 1-30-77

Cement circulated Yes No. of Sacks 200/50

Cemented by B J Witnessed by Lelan Mermis

Temp. Survey ran @ (AM) (PM) Date top cement @

Casing test @ (AM) (PM) Date

Method Used Witnessed by

Checked for shut off @ (AM) (PM) Date

Method used Witnessed by

Remarks: Lost Circ 283' no water Water 424-27, 721-76, 797-838

1130-80, 1208-45 Lost Circ & got it back. 1485-89, 1538-60 PD 2150-80

2230-75

Surface TD 360 1/8 17 1/2" hole Ran 9 jts 13 3/8" 48" H-40 but 300/sx Class C
PD 7:30 PM 1-23-77 Did not Circ. Hole filled w/Ready Mix.