

NEW MEXICO OIL CONSERVATION COMMISSION

DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <i>Western Oil Producers Inc.</i>		Lease <i>Hunker Com</i>		Well # <i>1</i>	
Location of Well	Unit/K <i>1980S+u</i>	Section <i>35</i>	Township <i>21</i>	Range <i>27</i>	County <i>Eddy</i>
Drilling Contractor <i>Hondo Drilling Co.</i>	Type of Equipment <i>Rotary to start 3-31-77</i>				

APPROVED CASING PROGRAM

* Witness

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<i>17 1/2"</i>	<i>13 3/8"</i>	<i>48</i>		<i>450</i>	<i>400 ctn.</i>
* <i>12 1/4"</i>	<i>8 5/8"</i>	<i>24</i>		<i>2650</i>	<i>1200 "</i>
<i>7 7/8"</i>	<i>5 1/2"</i>	<i>17+20</i>		<i>12000</i>	<i>1000</i>

Casing Data:

J. t.
Surface *66* joints of *8 5/8"* inch *24 1/2* # Grade *API New J.K. S.S.*

6 ft to 24 ft (Approved) (Rejected)

Inspected by *Lester Mermis* date *4-6-77*

Cementing Program

Size of hole *12 1/4" 1088* Size of Casing *8 5/8"* Sacks cement required *950/32*

Type of Shoe used *Anchor* Float collar used *Insert* Btm *2* jts *Threaded*

TD of hole *2636' 6"* Set *24 3/4'* Feet of *8 5/8"* inch *24 1/2* # Grade *J.K. S.S.*

New-used csg. @ *2636' 6"* with *200* sacks neat cement around shoe *Class C 2000*
+ *950/sax* *Thence to* additives *2% C.E.*

Plug down @ *2:45* (AM) (PM) Date *4-6-77*

Cement circulated *Yes* No. of Sacks *20/32*

Cemented by *H. H. Kuntze* Witnessed by *Lester Mermis*

Temp. Survey ran @ (AM) (PM) Date top cement @

Casing test @ (AM) (PM) Date

Method Used Witnessed by

Checked for shut off @ (AM) (PM) Date

Method used Witnessed by

Remarks: *425-555 salt - No loss circ at any kind.*