

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <i>Northern Natural Gas Co.</i>		Lease <i>Montroy A Com.</i>		Well # <i>1</i>	
Location of Well	Unit <i>K</i> <i>1980 S+W</i>	Section <i>5</i>	Township <i>20</i>	Range <i>26</i>	County <i>Eddy</i>
Drilling Contractor			Type of Equipment <i>Ready to start approx 9-5-77</i>		

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<i>17 1/2"</i>	<i>13 7/8"</i>	<i>54.5 #</i>		<i>350</i>	<i>500 ctn</i>
<i>12 1/4"</i>	<i>9 5/8"</i>	<i>40 #</i>		<i>1600</i>	<i>800 "</i>
<i>7 7/8"</i>	<i>4 1/2"</i>	<i>10.5+11.6 #</i>		<i>10000</i>	

Casing Data:

Int
~~Surface~~ *39* joints of *9 5/8* inch *47.43 40#* Grade *20 1/2 47 16 1/2 43 3 1/10"*
5-95 (Approved) (Rejected)

Inspected by *S. L. M. M. M.* date *9-23-77*

Cementing Program

Size of hole *12 1/4* Size of Casing *9 5/8* Sacks cement required *800/sk*

Type of Shoe used *widt* Float collar used *yes* Btm *2* jts *welded* *Thread lock*

TD of hole *1610' R03* Set *1594' 6L* Feet of *9 5/8* Inch *47.43 40#* Grade *5-95*

New-used csg. @ *1594' 6L* with *100/* sacks neat cement around shoe *Class C 2 1/2 50*
+ *200/sax RFC 3% cc additives 500/sx Lita 5# Kolite 1/4" Cello Flak = 2600*

Plug down @ *11:00* (AM) (PM) Date *9-24-77*

Cement circulated *yes* No. of Sacks *50/sk*

Cemented by *Dowell* Witnessed by *S. L. M. M. M.*

Temp. Survey ran @ (AM) (PM) Date top cement @

Casing test @ (AM) (PM) Date

Method Used Witnessed by

Checked for shut off @ (AM) (PM) Date

Method used Witnessed by

Remarks: *Possible water 74-84, 95-395, 420-579, 587-603, 613-19, 649-56*
692-821, 852-55, 883-946? 1165-80, 1228-1300, 1500-1510?