

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Gates Petr. Corp.</u>		Lease <u>Stonewall "EP" H. Com.</u>		Well # <u>4</u>	
Location of Well	Unit/H <u>1980 N 6600</u>	Section <u>30</u>	Township <u>20</u>	Range <u>28</u>	County <u>Eddy</u>
Drilling Contractor	<u>Moranco # 7</u>		Type of Equipment <u>Rotary to start 5-25-78</u>		

* witness

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>17 1/2"</u>	<u>13 7/8"</u>	<u>48</u>		<u>610</u>	<u>600 lbs.</u>
<u>12 1/4"</u>	<u>8 7/8"</u>	<u>24</u>		<u>2850</u>	<u>1400 "</u>
<u>7 7/8"</u>	<u>4 1/2 or 5 1/2"</u>			<u>11500</u>	<u>250</u>

Casing Data: 6-1-78

Surface joints of inch # Grade

(Approved) (Rejected)

Inspected by date

Cementing Program

Size of hole 12 1/4 Size of Casing 8 5/8 Sacks cement required

Type of Shoe used Texas Float collar used Insert Btm 3 jts welded Yes

TD of hole 2800 Set 8 7/8 Feet of Inch # Grade J-55

New ~~used~~ csg. @ 2800 with 1500 sacks neat cement around shoe

+ sax additives

Plug down @ 12:00 (AM) (PM) Date 6-1-78

Cement circulated NO No. of Sacks 1550 Sacks

Cemented by Hawco Witnessed by B.W. Weaver

Temp. Survey ran @ 6:00 (AM) (PM) Date 6-2-78 top cement @ 910 Ft

Casing test @ (AM) (PM) Date

Method Used Ran 1" Witnessed by B.W. Weaver

Checked for shut off @ (AM) (PM) Date

Method used Witnessed by

Remarks: 6-1-78 300 sack Hawco Thick Set 1100 Sack Hawco Lite

150 Sack Class C 6-2-78 Temperature Survey 910ft Top Cement

Ran 1" and circulated Cement 300 Class C 2% CC