

NEW MEXICO OIL CONSERVATION COMMISSION
 DRAWER DD
 ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Perry L. Bass</u>		Lease <u>Eggy Eddy Unit</u>		Well # <u>65</u>	
Location of Well	Unit <u>C</u>	Section <u>31</u>	Township <u>21</u>	Range <u>28</u>	County <u>Eddy</u>
Drilling Contractor	<u>McVay</u>		Type of Equipment <u>Pitman</u>		
Date <u>7-15-78</u>					

* Witness

APPROVED CASING PROGRAM

*

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>15"</u>	<u>11 3/4"</u>	<u>42</u>		<u>500</u>	<u>260 lbs.</u>
<u>11"</u>	<u>8 5/8"</u>	<u>20.28</u>		<u>3100</u>	<u>1050 lbs.</u>
<u>7 7/8"</u>	<u>5 1/2"</u>	<u>15.5417</u>		<u>12000</u>	<u>1250</u>

Casing Data:

Surface _____ joints of _____ inch _____ # Grade _____

(Approved) (Rejected)

Inspected by _____ date _____

Cementing Program

Size of hole 11" Size of Casing 8 5/8 Sacks cement required _____

Type of Shoe used point Float collar used yes Btm 3 jts welded yes

TD of hole 2884' Set 2884' Feet of 8 5/8 Inch 24.32 # Grade J-SS

New-used csg. @ 2884' with 200 sacks neat cement around shoe

+ _____ sack _____ additives _____

Plug down @ 12:45 (AM) (PM) Date 3/12/79

Cement circulated yes No. of Sacks 24

Cemented by Halliburton Witnessed by Mike Sturtevant

Temp. Survey ran @ _____ (AM) (PM) Date _____ top cement @ _____

Casing test @ _____ (AM) (PM) Date _____

Method Used _____ Witnessed by _____

Checked for shut off @ _____ (AM) (PM) Date _____

Method used _____ Witnessed by _____

Remarks: _____

Baskets @ 1110' - 1190'

centralizers @ 2870' - 2830' - 2790' - 2760' - 2730'

DV tool set @ 1150'

1st Pumped +300 sx Hall. lite 10# gilsonite - 1/4 floreal - 8# salt
+200 sx class C 290 cc

2nd Pumped +200 sx Hall lite 10# gilsonite - 1/4 floreal - 8# salt
+100 sx class C 290 cc