

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <i>Newbourne Oil Co.</i>		Lease <i>Marathon State</i>		Well # <i>1</i>	
Location of Well	Unit <i>660A 135C</i>	Section <i>30</i>	Township <i>20</i>	Range <i>27</i>	County <i>Eddy</i>
Drilling Contractor <i>-</i>		Type of Equipment <i>Rotary</i>			

APPROVED CASING PROGRAM

* *Witness*

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<i>17 1/2"</i>	<i>13 7/8"</i>	<i>48</i>		<i>500</i>	<i>500 cwt.</i>
<i>11"</i>	<i>8 5/8"</i>	<i>24</i>		<i>2100</i>	<i>525 cwt.</i>
<i>7 7/8"</i>	<i>4 1/2"</i>	<i>11.6</i>		<i>10800</i>	<i>440</i>

Casing Data:

Surface joints of *8 5/8* inch *24* # Grade *J-SS*
(Approved) (Rejected)

Inspected by *M.S.* date *10/4/79*

Cementing Program

Size of hole *12 1/4* Size of Casing *8 5/8* Sacks cement required

Type of Shoe used *guide* Float collar used *yes* Btm *8* jts welded *yes*

TD of hole *1932'* Set *1932'* Feet of *8 5/8* Inch *24* # Grade *J-SS*

New-used csg. @ *1932'* with *200* lbs. sacks neat cement around shoe

+ *850* sax *65-35-6* additives *1/2* # *celophane* - *5* # *zincite*

Plug down @ *5:30* (AM) (PM) Date *10/5/79*

Cement circulated *yes* No. of Sacks *50*

Cemented by *Western cementing* Witnessed by *Mike Stubblefield*

Temp. Survey ran @ (AM) (PM) Date top cement @

Casing test @ (AM) (PM) Date

Method Used Witnessed by

Checked for shut off @ (AM) (PM) Date

Method used Witnessed by

Remarks:

centralizers @ 1890'-1852'-1810'

Last Eddy break @ 1075'