

NEW MEXICO OIL CONSERVATION COMMISSION  
DRAWER DD  
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <i>Henneco Oil Co.</i>		Lessee <i>Catelan Draw Unit</i>		Well # <i>13</i>	
Location of Well	Unit <i>6605 19802</i>	Section <i>26</i>	Township <i>21</i>	Range <i>25</i>	County <i>Eddy</i>
Drilling Contractor			Type of Equipment <i>Rotary</i>		

APPROVED CASING PROGRAM

\* *witness*

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<i>17 1/2"</i>	<i>13 7/8"</i>	<i>48</i>		<i>350</i>	<i>275 cwt.</i>
<i>12 1/4"</i>	<i>8 5/8"</i>	<i>32</i>		<i>1900</i>	<i>530 cwt.</i>
<i>7 7/8"</i>	<i>5 1/2"</i>	<i>15.5-17</i>		<i>11100</i>	

Casing Data:

Surface \_\_\_\_\_ joints of *8 5/8* inch *32* # Grade *K-55*  
(Approved) (Rejected)

Inspected by *M.S.* date *4/18/80*

Cementing Program

Size of hole *12 1/4* Size of Casing *8 5/8* Sacks cement required \_\_\_\_\_

Type of Shoe used *Guide* Float collar used *Insert* Btm 3 jts welded *yes*

TD of hole *2098* Set *2098* Feet of *8 5/8* Inch *32* # Grade *K-55*

New ~~used~~ csg. @ *2098* with *200 SX* sacks neat cement around shoe

+ *2% cc* sax *200 Thickset* additives *#10 Galsomite, 1/4 Flo Seal, 2% Calcium Chloride*

Plug down @ *900* (AM) (PM) Date *4-18-80*

Cement circulated *yes* No. of Sacks *500 SX*

Cemented by *Henco* Witnessed by *B.W. Weaver*

Temp. Survey ran @ \_\_\_\_\_ (AM) (PM) Date \_\_\_\_\_ top cement @ \_\_\_\_\_

Casing test @ \_\_\_\_\_ (AM) (PM) Date \_\_\_\_\_

Method Used \_\_\_\_\_ Witnessed by \_\_\_\_\_

Checked for shut off @ \_\_\_\_\_ (AM) (PM) Date \_\_\_\_\_

Method used \_\_\_\_\_ Witnessed by \_\_\_\_\_

Remarks: *850 SX Henco Lite #5 LB Gilsomite 1/4 Flo Seal, 3% Calcium Chloride*

*Centralizers @ 2078 - 2058 Basket @ 1186, 1233, 1279*

*Loss Circulation @ 1244 Last Drilling Break @ 2040*