

NEW MEXICO OIL CONSERVATION COMMISSION  
DRAWER DD  
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <b>YATES DET. CO</b>			Lease <b>STDNEWALL WM ST.</b>		Well # <b>2</b>
Location of Well	Unit <b>P</b>	Section <b>30</b>	Township <b>20 S</b>	Range <b>28 E</b>	County <b>EDDY</b>
Drilling Contractor	<b>L/M</b>		Type of Equipment <b>ROTARY</b>		

\* Witness

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
17 1/2"	13 3/8"	48#	NEW	550'	CIRC
12 1/4"	8 5/8"	24-28#	"	* 2400	CIRC
7 7/8"	5 1/2"	17-20#	"	TD	650

Casing Data: \* OR TO BASE OF REEF.

Surface \_\_\_\_\_ joints of \_\_\_\_\_ inch \_\_\_\_\_ # Grade \_\_\_\_\_  
(Approved) (Rejected)

Inspected by \_\_\_\_\_ date \_\_\_\_\_

Cementing Program

Size of hole 12 1/4 Size of Casing 8 5/8 Sacks cement required \_\_\_\_\_

Type of Shoe used Tex-Rat Float collar used Insert Btm 3 jts welded yes

TD of hole 2410 Set 2416 Feet of 8 5/8 Inch 24 # Grade J-55

New-used csg. @ 2416 with 400 sacks neat cement around shoe

+ 500 sax Class C additives 4% G-1 2% CC

Plug down @ 11:00 (AM) (PM) Date 10-6-83

Cement circulated No No. of Sacks \_\_\_\_\_

Cemented by Western Witnessed by BWW

Temp. Survey ran @ 5:00 (AM) (PM) Date 10-6-83 top cement @ 365

Casing test @ \_\_\_\_\_ (AM) (PM) Date \_\_\_\_\_

Method Used \_\_\_\_\_ Witnessed by \_\_\_\_\_

Checked for shut off @ \_\_\_\_\_ (AM) (PM) Date \_\_\_\_\_

Method used \_\_\_\_\_ Witnessed by \_\_\_\_\_

Remarks:

Ran 1" to 390 ft and circulated cement 150 SX Class C 3% CC

Finish @ 6:30 PM