

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Yates Pet. Co.</u>			Lease <u>Stonewall WM ST.</u>		Well # <u>4</u>
Location of Well	Unit <u>M</u>	Section <u>30</u>	Township <u>20S</u>	Range <u>28E</u>	County <u>Eddy</u>
Drilling Contractor	<u>LARUE</u>		Type of Equipment <u>ROTARY</u>		
<p>* Witness <u>APPROVED CASING PROGRAM</u></p>					
Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>17 1/2</u>	<u>13 3/8"</u>	<u>48#</u>	<u>NEW</u>	<u>550'</u>	<u>CIRC</u>
* <u>12 1/4</u>	<u>8 5/8"</u>	<u>24-28#</u>	<u>"</u>	<u>2500</u>	<u>CIRC</u>
<u>7 7/8</u>	<u>5 1/2"</u>	<u>17-20#</u>	<u>"</u>	<u>TD</u>	<u>650 SK</u>
Casing Data:					
Surface _____ joints of _____ inch _____ # Grade _____					
(Approved) (Rejected) _____					
Inspected by _____ date _____					
Cementing Program					
Size of hole <u>12 1/4</u> Size of Casing <u>8 5/8</u> Sacks cement required <u>1300</u>					
Type of Shoe used <u>TEX. PT.</u> Float collar used <u>INST.</u> Btm 3 jts welded <u>YES</u>					
TD of hole <u>2462</u> Set <u>2463</u> Feet of <u>8 5/8</u> Inch <u>24</u> # Grade <u>J-55</u>					
New-used csg. @ <u>2462</u> with <u>300</u> sacks neat cement around shoe c/c 2% CaCl ₂					
+ <u>900</u> sax <u>PACSETER LITE</u> additives <u>1/4"</u> celloceal, <u>5#</u> Gilsonite, <u>3%</u> CaCl ₂					
Plug down @ <u>10:30</u> (AM) (PM) <u>PM</u> Date <u>6/5/83</u>					
Cement circulated <u>yes</u> No. of Sacks <u>40 SKS.</u>					
Cemented by <u>WESTERN</u> Witnessed by <u>Randy Brooks</u>					
Temp. Survey ran @ _____ (AM) (PM) Date _____ top cement @ _____					
Casing test @ _____ (AM) (PM) Date _____					
Method Used _____ Witnessed by _____					
Checked for shut off @ _____ (AM) (PM) Date _____					
Method used _____ Witnessed by _____					
Remarks: <u>+100 SKS. Thixolite + 1/2#/sk. Permac. + 10#/sk. Gilsonite</u>					