

# FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>MOBILE PETROLEUM</u>		Lease <u>MOBILE PETROLEUM</u>		Well # <u>1</u>	
Location of Well	Unit <u>A</u>	Section <u>6</u>	Township <u>4N</u>	Range <u>4E</u>	County <u>SECOY</u>
Drilling Contractor <u>W.A.</u>			Type of Equipment <u>EDGE</u>		

**\* WITNESS**

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cemen
<u>17 1/2</u>	<u>13 1/8"</u>	<u>42 #</u>	<u>NEW</u>	<u>450</u>	<u>600</u>
<u>* 12 1/4</u>	<u>8 5/8"</u>	<u>24 #</u>	<u>"</u>	<u>2600</u>	<u>400</u>
<u>7 1/8</u>	<u>5 1/2"</u>	<u>14 #</u>	<u>"</u>	<u>450</u>	<u>1000</u>

Casing Data:

Surface \_\_\_\_\_ joints of \_\_\_\_\_ inch \_\_\_\_\_ # Grade \_\_\_\_\_  
 \_\_\_\_\_ (Approved) (Rejected) \_\_\_\_\_

Inspected by \_\_\_\_\_ date \_\_\_\_\_

Cementing Program

Size of hole 12 1/4 Size of Casing 8 5/8 Sacks cement required \_\_\_\_\_

Type of Shoe used GOLF Float collar used INSERT Btm 3 jts welded Yes

ID of hole 2599 Set 2601 Feet of 8 5/8 Inch 48 # Grade J-55

New-used csg. @ 2599 with 200 sacks neat cement around shoe 2% CaCl<sub>2</sub>  
 + 1000 sax H-lite additives 5 # GILS, 1/4 # Flocele, + 100 SxS H-lite Thixset.

Plug down @ 9:30 (AM) (PM) Date 2/25/84

Cement circulated 2 1/2 No. of Sacks 200 SxS

Cemented by Halliburton Witnessed by Fanny Brown

Temp. Survey ran @ \_\_\_\_\_ (AM) (PM) Date \_\_\_\_\_ top cement @ \_\_\_\_\_

Casing test @ \_\_\_\_\_ (AM) (PM) Date \_\_\_\_\_

Method Used \_\_\_\_\_ Witnessed by \_\_\_\_\_

Checked for shut off @ \_\_\_\_\_ (AM) (PM) Date \_\_\_\_\_

Method used \_\_\_\_\_ Witnessed by \_\_\_\_\_

Remarks: \_\_\_\_\_