

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER 100
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator MONSANTO OIL CO		Lease Burton Flat Deep UT.		Well # 24	
Location of Well	Unit A	Section 2	Township 21	Range 27	County EDDY
Drilling Contractor	N/A		Type of Equipment ROTARY		

* Witness

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
17 1/2"	13 3/8"	48.0 #	NEW	500	CIRC
* 11"	8 5/8"	24.0 #	"	2500±	CIRC
7 7/8"	5 1/2"	15.5 #	"	5700	750 SXS.

Casing Data:

Surface 62 joints of 8 5/8 inch 24 # Grade J-55

yes (Approved) (Rejected)

Inspected by BW Weaver date 4-10-84

Cementing Program

Size of hole 11 Size of Casing 8 5/8 Sacks cement required 200

Type of Shoe used Tex-Par Float collar used Collar Btm 3 jts welded yes

TD of hole 2560 Set 2572 Feet of 8 5/8 Inch 24 # Grade J-55

New-used csg. @ 2572 with 200 sacks neat cement around shoe

+ 700 sax Hawco Thukfit additives 1000 SK Hawco lite

Plug down @ 9:00 (AM) (PM) Date 4-10-84

Cement circulated NO No. of Sacks

Cemented by Hawco Witnessed by BW Weaver

Temp. Survey ran @ 3:00 (AM) (PM) Date 4-10-84 top cement @ 1200

Casing test @ (AM) (PM) Date

Method Used Witnessed by BW Weaver

Checked for shut off @ (AM) (PM) Date

Method used Witnessed by

Remarks: Loss zone @ 1500

Ran 1" to 991 Cement WITH 75SX C 4% CC

Tag @ 911 Cement 75SX C 4% CC

Tag @ 911 Cement 100 SX C 4% CC

Tag @ 891 Cement 100 SX C 4% CC

Tag @ 841 Cement 150 SX C 2% CC

Tag @ 811 Cement 125 SX C 2% CC

Tag @ 790 Cement 150 SX C 2% CC

Tag @ 773 Cement 225 SX C 2% CC

Tag @ 609 Circ Cement 200 SX C 4% CC