

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Exxon</u>			Lease <u>N.M. DP ST</u>		Well # <u>3</u>
Location of Well	Unit <u>E</u>	Section <u>28</u>	Township <u>20</u>	Range <u>28</u>	County <u>EDDY</u>
Drilling Contractor	<u>UNK</u>		Type of Equipment <u>ROTARY</u>		

* Witness

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot #	New or Used	Depth	Sacks Cement
<u>26 1/2"</u>	<u>20"</u>	<u>94</u>	<u>NEW</u>	<u>40'</u>	<u>CIRC</u>
<u>17 1/2"</u>	<u>13 3/8"</u>	<u>54.5</u>	<u>"</u>	<u>600'</u>	<u>"</u>
* <u>11"</u>	<u>8 5/8"</u>	<u>24.0</u>	<u>"</u>	<u>2500'</u>	<u>"</u>
<u>7 7/8"</u>	<u>5 1/2"</u>	<u>14-15.5</u>	<u>"</u>	<u>5300'</u>	<u>1400 SX.</u>

Casing Data:

Surface joints of 8 7/8 inch 24 # Grade J-55

Yes (Approved) (Rejected)

Inspected by BW Weaver date 3-12-84

Cementing Program

Size of hole 11 Size of Casing 300 Sacks cement required

Type of Shoe used Tox-Pat Float collar used Insert Btm 3 jts welded yes

TD of hole 2544 Set 2541 Feet of 8 7/8 Inch 24 # Grade J-55

New-used csg. @ 2541 with 300 sacks neat cement around shoe

+ 700 sax Dowell 1.0% additives

Plug down @ 9:30 (AM) (PM) Date 3-12-84

Cement circulated No No. of Sacks

Cemented by Dowell Witnessed by BW Weaver

Temp. Survey ran @ 3:30 (AM) (PM) Date 3-12-84 top cement @ 841

Casing test @ (AM) (PM) Date

Method Used Witnessed by

Checked for shut off @ (AM) (PM) Date

Method used Witnessed by

Remarks: Loss zones @ 1048 - 1065 - 1248

Ran 1" to 625 and circulated cement with 215 SX class c