

ATTACHMENT I

Item 32

Acid, Shot, Fracture, Cement Squeeze

<u>Depth Interval</u>	<u>Amount & Kind of Material Used</u>
10,258'-10,594'	Perf - 2 JSPF (total 63 holes)
5410'	Perf - 4 JSPF squeeze holes
5410'-Surface	Cement - 1450 sx Howco Lite & Class "C". Good returns to surface between 4 1/2" & 8 5/8" but did not circ cement. Tested squeeze perfs @ 5410' to 3500 psig. Held OK.
8952'-60'	Squeeze perfs (Wolfcamp) w/50 sx Class "H" premium & 50 sx Class "H" Neat. Final squeeze press. 3600 psig. Tested squeeze to 1800 psig. Held OK.