

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Monsanto</u>		Lease <u>Burton Hat Deep. Ut. E</u>		Well # <u>27</u>	
Location of Well	Unit <u>G</u>	Section <u>2</u>	Township <u>21 S</u>	Range <u>27 E</u>	County <u>Eddy</u>
Drilling Contractor	<u>N/A</u>		Type of Equipment <u>ROTARY</u>		

APPROVED CASING PROGRAM

*** WITNESS**

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cemen
<u>17 1/2"</u>	<u>13 3/8"</u>	<u>48.0 #</u>	<u>NEW</u>	<u>600'</u>	<u>CIRC</u>
* <u>11"</u>	<u>8 5/8"</u>	<u>24.0 #</u>	<u>"</u>	<u>2500'</u>	<u>CIRC</u>
<u>7 7/8"</u>	<u>5 1/2"</u>	<u>15.5 #</u>	<u>"</u>	<u>5700'</u>	<u>750 SX</u>

Casing Data:

Surface 65 joints of 8 5/8 inch 24 # Grade J-55

yes (Approved) (Rejected)

Inspected by B.W. Weaver date 4-24-84

Cementing Program

Size of hole 11 Size of Casing 8 5/8 Sacks cement required 200

Type of Shoe used Guide Float collar used Insert Btm 3 jts welded yes

TD of hole 2573 Set 2573 Feet of 8 5/8 Inch 24 # Grade J-55

New-used csg. @ 2573 with 200 sacks neat cement around shoe

+ 400 sax Thicket additives 800 SX Hawco Lite #6 Gilsomite 1/2 Flo Seal 2% CC

Plug down @ 8:15 (AM) (PM) Date 4-24-84

Cement circulated yes No. of Sacks 160

Cemented by Hawco Witnessed by B.W. Weaver

Temp. Survey ran @ (AM) (PM) Date top cement @

Casing test @ (AM) (PM) Date

Method Used Witnessed by

Checked for shut off @ (AM) (PM) Date

Method used Witnessed by

Remarks: Loss Zone @ 1385 @ 1921