

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Eng. 12-18-84

Operator Getty		Lease Getty 1B32 st		Well # 1-Y	
Location of Well	Unit LM	Section 32	Township 21	Range 24	County Eddy
Drilling Contractor	N/A		Type of Equipment Rotary		

* = CSG. TO WITNESS

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cemen
11 1/2	13 3/8	48#	New	300'	Circ.
12 1/4	9 5/8	32.3#	"	2400'	Circ.
8 1/2	1"	23# 26	"	9140'	Circ.

Casing Data:

Surface _____ joints of 9 7/8 inch 32 # Grade J-55
 _____ (Approved) (Rejected) _____

Inspected by BW Weaver date 1-2-85

Cementing Program

Size of hole 12 1/4 Size of Casing 9 7/8 Sacks cement required 200

Type of Shoe used Tex-Pat Float collar used Float Collar Btm 3 jts welded yes

TD of hole 2400 Set 2411 Feet of 9 7/8 Inch 32 # Grade J-55

New-used csg. @ 2411 with 200 sacks neat cement around shoe

+ 1000 sax Class H 16% Jel additives 1/2 LB Flo Seal #10 Gilsonite 2% CC

Plug down @ 2100 (AM) (PM) Date 1-3-84

Cement circulated No No. of Sacks _____

Cemented by Howco Witnessed by BW Weaver

Temp. Survey ran @ 9:00 (AM) (PM) Date 1-3-85 top cement @ 1175

Casing test @ _____ (AM) (PM) Date _____

Method Used _____ Witnessed by _____

Checked for shut off @ _____ (AM) (PM) Date _____

Method used _____ Witnessed by _____

Remarks: Ran 1" to 580 50 SX Class H 2% CC

100 SX Class H 2% CC

100 SX Class H 2% CC

150 SX class H 2% Circulate Cement