

FIELD REPORT FOR CEMENTING OF WELLS

OIL CONSERVATION DIVISION

Operator <u>Gates Petr. Corp.</u>		Lease <u>Airport West "AGL" Com</u>		Well # <u>1</u>	
Location of Well	Unit <u>0</u>	Section <u>29</u>	Township <u>22</u>	Range <u>26</u>	County <u>Eddy</u>
Drilling Contractor	<u>Undesignated</u>		Type of Equipment <u>Rotary</u>		

*** Witness 13 3/8** APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>26</u>	<u>20</u>	<u>94#</u>		<u>350</u>	<u>300</u>
<u>17 1/2</u>	<u>*13 3/8</u>	<u>54.5</u>		<u>1600</u>	<u>500</u>
<u>12 1/4</u>	<u>9 7/8</u>	<u>32</u>		<u>2700</u>	<u>900</u>
<u>8 3/4</u>	<u>5 1/2</u>	<u>17 + 20</u>		<u>TD</u>	<u>500</u>

Casing Data:

Surface _____ joints of _____ inch _____ # Grade _____
 _____ (Approved) (Rejected) _____

Inspected by _____ date _____

Cementing Program

Size of hole 17 1/2 Size of Casing 13 3/8" Sacks cement required _____

Type of Shoe used guide Float collar used yes Btm 3 jts welded yes

TD of hole 1650' Set 1650' Feet of 13 3/8" Inch 54 # Grade J-55

New-used csg. @ 1650' with 300 32cc sacks neat cement around shoe
 + 300 sack thix-set additives _____

Plug down @ 8:00 (AM) (PM) (PM) Date 8-19-89

Cement circulated yes No. of Sacks 230 sx.

Cemented by Western Co. Witnessed by M.S.

Temp. Survey ran @ _____ (AM) (PM) Date _____ top cement @ _____

Casing test @ _____ (AM) (PM) Date _____

Method Used _____ Witnessed by _____

Checked for shut off @ _____ (AM) (PM) Date _____

Method used _____ Witnessed by _____

Remarks: +1150 sx Pacemaker Lite (12# gilsonite)

2 baskets - 1014' - 879' Last dily break @ 1305'