

FIELD REPORT FOR CEMENTING OF WELLS

OIL CONSERVATION DIVISION

30-015-28197

Operator <u>Primera Oper. Inc.</u>		Lease <u>Fanning Draw St.</u>		Well # <u>1</u>	
Location of Well	Unit <u>0</u>	Section <u>32</u>	Township <u>21</u>	Range <u>22</u>	County <u>Eddy</u>
Drilling Contractor	<u>NA</u>		Type of Equipment <u>Rotary</u>		

APPROVED CASING PROGRAM

* Witness

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
17 1/2	* 13 3/8	54.5		400	400 Circ
12 1/4	* 8 5/8	24		1900	1200 Circ
7 7/8	5 1/2	15 1/2 + 17		7300	800

Casing Data:

Surface _____ joints of 8 5/8" inch 24 # Grade J-55

(Approved) (Rejected)

Inspected by M.S. date _____

Cementing Program

Size of hole 12 1/4" Size of Casing 8 5/8" Sacks cement required _____Type of Shoe used guide Float collar used insert Btm 3 jts welded yesTD of hole 1920' Set 1920' Feet of 8 5/8" Inch 24 # Grade J-55(New) used csg. @ 1920' with 200 sacks neat cement around shoe+ 250 sack Hall. Lile - C additives 10 # gilsonite, 1/4 # celoseal,Plug down @ 12:00 (AM) (PM) Date _____Cement circulated No No. of Sacks - 0 -Cemented by Halliburton Witnessed by Mike StubblefieldTemp. Survey ran @ 6:00 (AM) (PM) Date _____ top cement @ 169' *

Casing test @ _____ (AM) (PM) Date _____

Method Used _____ Witnessed by _____

Checked for shut off @ _____ (AM) (PM) Date _____

Method used _____ Witnessed by _____

Remarks: +200sx this set 10 # gilsonite, 1/4 # celoseal,

WT 1390' - 1490'

L.O.B. - 1490'

* See 1" on reverse side

1. Run 1" + Tagged to c @ 560'
entered w/ 50 sx 470cc

fluid level @ 80'

2. Run 1" + Tagged to c @ 480'
entered w/ 50 sx 470cc

3. Run 1" + Tagged to c @ 460'
entered w/ 50 sx 470cc

4. Run 1" + Tagged to c @ 360'
entered w/ 150 sx cl. c. 270cc

5. to c @ 60'

Blend-mixed to surface.

total 6 1/2 yards.