

CASING PROGRAM CONT.

<u>String</u>	<u>Depth Interval</u>	<u>Size</u>	<u>Weight</u>	<u>Grade</u>	<u>Cplg.</u>	<u>Drift Diameter</u>
---------------	---------------------------	-------------	---------------	--------------	--------------	---------------------------

CEMENTING PROGRAM

0-100±	13-3/8" surface - 17-1/2" hole	Note:	Volume of cement will be adjusted as required by prudent practices. Will circulate.
	100 sks. HLW w/5 #/sk. Gilsonite		
	1/4 #/sk. Flocele		
	4% CaCl		
	50 sks. C w/1/4 #sk. Flocele		
	4% CaCl		
0-1600±	8-5/8" Intermediate - 12-1/4" hole	Note:	Same as above.
	600 sks. HLW w/5 #/sk. Gilsonite		
	1/4 #/sk. Flocele		
	2% CaCl		
	150 sks. C w/1/4 #/sk. Flocele		
	2% CaCl		
0-6300±	5" Production - 7-7/8" hole		
	300 sks. HLW w/5 #/sk. Gilsonite		
	1/4 #/sk. Flocele		
	2% CaCl		
	400 sks. H w/2% CaCl		
	1/4 #/sk. Flocele		