

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <i>Bellco Petr Corp.</i>		Lease <i>John Jayce Com.</i>		Well # <i>1</i>	
Location of Well	Unit <i>2307 N 1740 W</i>	Section <i>5</i>	Township <i>22</i>	Range <i>27</i>	County <i>El Paso</i>
Drilling Contractor			Type of Equipment <i>Rotary to start June 15 - 1974</i>		

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<i>200 14 3/4</i>	<i>16" 10 3/4</i>	<i>65 45.5</i>		<i>350 2000</i>	<i>450 950</i>
<i>9 1/2"</i>	<i>7 5/8"</i>	<i>26.4</i>		<i>8950</i>	<i>350</i>
<i>6 1/2"</i>	<i>5 1/2" liner</i>	<i>20</i>		<i>11600</i>	<i>250</i>

Casing Data:

Surface *4.5* joints of *10 3/4* inch *45.5* # Grade *API New K-55*

24 to 51 K-55 (Approved) (Rejected) *46.5 - 20.5 K-55, 2 to 46.5*

Inspected by *J. A. Mermis* date *6-22-74*

Cementing Program

Size of hole *13 3/4"* Size of Casing *10 3/4"* Sacks cement required *1150*

Type of Shoe used *Guide* Float collar used *Insert Btm 2 jts welded Thread L.L.*

TD of hole *1700 R/S* *1683' GL* Feet of *10 3/4* Inch *45.5* # Grade

New-used csg. @ *1683' GL* with *200* sacks neat cement around shoe *2% cc 11.8"*

+ *9.50* sack *Amoco* additives *5" Glycerite 12.8, 13.0"*

Plug down @ *9:50* (AM) (PM) Date *6-22-74*

Cement circulated *Yes* No. of Sacks *150/50*

Cemented by *Halliburton* Witnessed by *J. A. Mermis*

Temp. Survey ran @ (AM) (PM) Date top cement @

Casing test @ (AM) (PM) Date

Method Used Witnessed by

Checked for shut off @ (AM) (PM) Date

Method used Witnessed by

Remarks: *TD 350' 20" hole 16" New H-40 65" 47 3/4"*

Class C 2% cc Cmc 50/50 4:15 AM 6-18-74