

Maddox Energy Corporation

Pardue 27 No. 1

Proposed Cementing Program

Surface - 450', 20"

675 sacks Class "C" w/3% CaCl₂

First Intermediate - 3000', 13 3/8"

2200 sacks Halliburton Light
with 1/4# flocc and 8 # salt
per sack

200 sacks Class "C" next

Second Intermediate - 10,400', 9 5/8"

1) First stage, 10400' - 5800' - 1050 sacks
Trinity Lite with 1/4# flocc/sack and
0.5% CFR-2

300 sacks Class "H" with 0.5% CFR-2

2) Second stage, 5800' - surface - 1250
sacks Trinity Lite with 0.5% CFR-2

200 sacks Class "H" with 0.5% CFR-2

First Liner - 10,150 to 12350', 7"

300 sacks Class H with 3/4% CFR-2 & 5# KCl/sx

Second Liner - 12,100' to 13,300', 4 1/2"

100 sacks Class H with 1% CFR-2 & 5# KCl/sx