

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>W A Moncrief Jr</u>		Lease <u>Crooked Creek State Com</u>		Well # <u>1</u>	
Location of Well	Unit <u>1980S</u> <u>1980W</u> <u>K</u>	Section <u>1</u>	Township <u>24</u>	Range <u>24</u>	County <u>Eddy</u>
Drilling Contractor	<u>to be determined</u>		Type of Equipment <u>Rotary</u> <u>ASAP</u>		

* Witness

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>17 1/2"</u>	<u>13 3/8"</u>	<u>48# H-40 ST+C</u>		<u>400'</u>	<u>400 SX - Circ</u>
<u>11 1/2"</u>	<u>8 5/8"</u>	<u>32# K-55 ST+C</u>		<u>2700'</u>	<u>1000 SX - Circ</u>
<u>7 7/8"</u>	<u>4 1/2"</u>	<u>11.6# N-80 LT+C</u>		<u>10,700</u>	<u>500 SX -</u>

Casing Data:

Surface _____ joints of _____ inch _____ # Grade _____
(Approved) (Rejected)

Inspected by _____ date _____

Cementing Program

Size of hole 12 1/4 Size of Casing 8 5/8 Sacks cement required _____

Type of Shoe used Guide Float collar used Float Collar 3 jts welded yes

TD of hole 2705 Set 2730 Feet of 8 5/8 Inch 32 # Grade K 55

New-~~used~~ csg. @ 2730 with 200 sacks neat cement around shoe
+ 950 sax Hawco Lite additives #6 Gilsenite 1/4" Fla Seal

Plug down @ 7:00 (AM) (PM) Date 8-15-81

Cement circulated yes No. of Sacks 190

Cemented by Hawco Witnessed by BWUwawer

Temp. Survey ran @ _____ (AM) (PM) Date _____ top cement @ _____

Casing test @ _____ (AM) (PM) Date _____

Method Used _____ Witnessed by _____

Checked for shut off @ _____ (AM) (PM) Date _____

Method used _____ Witnessed by _____

Remarks: _____