

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Exxon Corp.</u>		Lease <u>N.M. DI ST. #</u>		Well # <u>3</u>	
Location of Well	Unit <u>Ut. L</u>	Section <u>19</u>	Township <u>23</u>	Range <u>26</u>	County
Drilling Contractor	<u>N/A</u>		Type of Equipment <u>ROTARY</u>		
* Witness <u>APPROVED CASING PROGRAM</u>					
Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>20"</u>	<u>16"</u>	<u>65#</u>	<u>NEU</u>	<u>60'</u>	<u>CIRC</u>
* <u>14 3/4"</u>	<u>10 3/4"</u>	<u>40.5</u>	<u>"</u>	<u>1600'</u>	<u>CIRC</u>
<u>7 7/8"</u>	<u>5 1/2"</u>	<u>14#</u>	<u>"</u>	<u>5700'</u>	<u>Tie bk.</u>
Casing Data:					
Surface <u> </u> joints of <u> </u> inch <u> </u> # Grade <u> </u>					
<u> </u> (Approved) (Rejected) <u> </u>					
Inspected by <u> </u> date <u> </u>					
Cementing Program					
Size of hole <u>12 1/4</u> Size of Casing <u>8 5/8</u> Sacks cement required <u> </u>					
Type of Shoe used <u>Guide</u> Float collar used <u>Flat Collar</u> Btm 3 jts welded <u>Yes</u>					
TD of hole <u>1435</u> Set <u>1440</u> Feet of <u>8 5/8</u> Inch <u>24</u> # Grade <u>J-55</u>					
New-used csg. @ <u>1440</u> with <u>400</u> sacks neat cement around shoe					
+ <u>650</u> sax <u>BJ lite</u> additives <u>2nd Stage SSD SX BJ lite + 100 SX C 2% CC</u>					
Plug down @ <u>6:30</u> (AM) (PM) Date <u>12-4-83</u>					
Cement circulated <u>N0</u> No. of Sacks <u> </u>					
Cemented by <u>BJ</u> Witnessed by <u>BW. Weaver</u>					
Temp. Survey ran @ <u>12:30</u> (AM) (PM) Date <u>12-4-83</u> top cement @ <u>650</u>					
Casing test @ <u> </u> (AM) (PM) Date <u> </u>					
Method Used <u> </u> Witnessed by <u> </u>					
Checked for shut off @ <u> </u> (AM) (PM) Date <u> </u>					
Method used <u> </u> Witnessed by <u> </u>					
Remarks: <u>Run 1" to 680 100 SX C 3% CC</u>					
<u>Tag @ 680 50 SX C 3%</u>					
<u>Tag @ 680 50 SX C 3%</u>					
<u>Tag @ 680 50 SX C 3%</u>					

Tag @ 680	150 SX C 3%	1 yd Gravel	TOTAL CMT 5220 1 + 2 Stg 1200 27 YDS REDMIX 60 YDS PEA GRAVEL 20 YDS SAND
Tag @ 680	200 SX C 3%	1 yd Gravel	
Tag @ 680	200 SX C 2%	1 yd Gravel	
Tag @ 840	200 SX C 2%	1 yd Gravel	
Tag @ 840	200 SX C 2%	1 yd Gravel	
Tag @ 800	20 SX C 2%		
Tag @ 840	300 SX C 2%	8 yd Gravel	
Tag @ 840	300 SX C 2%	8 yd Gravel	
Tag @ 840			
Tag @ 840			

over

Tag @ 840 300 SX C 2% CC 8 yd Gravel

Tag @ 840 300 SX C 2% CC 8 yd Gravel

Tag @ 840 300 SX C 2% CC 8 yd Gravel

Tag @ 840 300 SX C 2% 10 yd Gravel 10 yd sand

Tag @ 820 200 SX Class H 9% A2 + 1% D-31 (Sure Plug)

Tag @ 560 400 SX Class C

Tag @ 560 200 SX Sure Plug

Tag @ 540 50 SX C 2% CC #10 sand

Tag @ 528 150 SX C 2% CC

Tag @ 819 9 yd Red-Mix

Tag @ 774 18 yd Red Mix

Tag @ 378 220 SX Class C 2% CC Circulate Cement