

NEW MEXICO OIL CONSERVATION COMMISSION  
DRAWER DD  
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

|                            |               |                   |                                 |                 |                    |
|----------------------------|---------------|-------------------|---------------------------------|-----------------|--------------------|
| Operator <u>Exxon Corp</u> |               |                   | Lease <u>NM 01 ST. #</u>        |                 | Well # <u>2</u>    |
| Location of Well           | Unit <u>D</u> | Section <u>19</u> | Township <u>23</u>              | Range <u>26</u> | County <u>EDDY</u> |
| Drilling Contractor        | <u>NA</u>     |                   | Type of Equipment <u>ROTARY</u> |                 |                    |

**\* Witness** APPROVED CASING PROGRAM

| Size of Hole     | Size of Casing | Weight Per Foot         | New or Used | Depth        | Sacks Cement         |
|------------------|----------------|-------------------------|-------------|--------------|----------------------|
| <u>20"</u>       | <u>16"</u>     | <u>65<sup>#</sup></u>   | <u>NEW</u>  | <u>60'</u>   | <u>CIRC.</u>         |
| <u>* 14 3/4"</u> | <u>10 3/4"</u> | <u>40.5<sup>#</sup></u> | <u>"</u>    | <u>1600'</u> | <u>CIRC</u>          |
| <u>7 7/8"</u>    | <u>5 1/2"</u>  | <u>14<sup>#</sup></u>   | <u>"</u>    | <u>5400'</u> | <u>Tie bk to int</u> |

Casing Data:

Surface 36 joints of 10 3/4 inch 40.5<sup>#</sup> Grade J-55  
Yes (Approved) (Rejected)

Inspected by BW Weaver date 10-24-83

Cementing Program

Size of hole 12 3/4 Size of Casing 10 3/4 Sacks cement required     

Type of Shoe used Guide Float collar used FLAT 4 1/2 Btm 3 jts welded yes

TD of hole 1450 Set 1466 Feet of 10 3/4 Inch 40.5<sup>#</sup> Grade J-55

New-used csg. @ 1466 with 400 sacks neat cement around shoe  
+ 1600 sax BJ lite additives 1/4 Flo Seal

Plug down @ 11:30 (~~AM~~) (PM) Date 10-24-83

Cement circulated Yes No. of Sacks 500

Cemented by B.J. Hughes Witnessed by BW Weaver

Temp. Survey ran @      (AM) (PM) Date      top cement @     

Casing test @      (AM) (PM) Date     

Method Used      Witnessed by     

Checked for shut off @      (AM) (PM) Date     

Method used      Witnessed by     

Remarks: Loss zone @ 200-332