

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Exxon Oil Corp.</u>		Lease <u>N.M. E.R. ST. Com.</u>		Well # <u>1</u>	
Location of Well	Unit <u>I</u>	Section <u>36</u>	Township <u>23</u>	Range <u>25</u>	County <u>Elddy</u>
Drilling Contractor	<u>Hondo rig #9</u>		Type of Equipment <u>Rotary</u>		
APPROVED CASING PROGRAM					
Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
Casing Data:					
Surface _____ joints of _____ inch # _____ Grade _____ (Approved) (Rejected) _____					
Inspected by _____ date _____					
Cementing Program					
Size of hole <u>12 1/4"</u> Size of Casing <u>8 5/8"</u> Sacks cement required _____					
Type of Shoe used <u>guide</u> Float collar used <u>insert</u> Btm 3 jts welded <u>yes</u>					
TD of hole <u>1910'</u> Set <u>1910'</u> Feet of <u>8 5/8"</u> Inch <u>24</u> # Grade <u>J-SS</u>					
New used csg. @ <u>1910'</u> with <u>400</u> sacks neat cement around shoe					
+ _____ sax _____ additives _____					
Plug down @ <u>10:00</u> (AM) (PM) Date <u>5/30/85</u>					
Cement circulated <u>No</u> No. of Sacks <u>-0-</u>					
Cemented by <u>Halliburton</u> Witnessed by <u>Mike Stullfeld</u>					
Temp. Survey ran @ _____ (AM) (PM) Date _____ top cement @ _____					
Casing test @ _____ (AM) (PM) Date _____					
Method Used _____ Witnessed by _____					
Checked for shut off @ _____ (AM) (PM) Date _____					
Method used _____ Witnessed by _____					
Remarks: <u>DV tool @ 1288'</u>					
<u>Cement bridged while displacing 1st stage cement. toc @ 1100'. Drilled out</u>					
<u>cut from csg & ran CBL. Toc @ 1400'. lost circ. zone 1383'</u>					
<u>last July break @ 1740'</u>					

1. Run 1" + Tagged Toc @ 1400'
w/ 200 sr cl. C 270 cc

2. Run 1" + Tagged toc @ 1400'
w/ 35 sr cl. C 270 cc

3. Run 1" to 1150' + dropped
1" in hole.

Run 1" to 848' could not get past bridge.
Tried to fill hole w/ water. Did not fill.
pumped 300 sr Hal. Lite

4. Run 1" + Tagged @ 848'
w/ 400 sr Hal. Lite

5. Run 1" + Tagged Toc @ 842'
w/ 100 sr cl. C.

6. Run 1" + Tagged Toc @ 660'
w/ 241 sr cement circ. to surface.